

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Yates Petr. Corp.</u>		Lease <u>Pauline ALB St.</u>		Well # <u>1</u>	
Location of Well	Unit <u>I</u>	Section <u>32</u>	Township <u>23</u>	Range <u>31</u>	County <u>Eddy</u>
Drilling Contractor	<u>Undesignated</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

* Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>* 13 3/8</u>	<u>54.5 #</u>		<u>500</u>	<u>700 Circ</u>
<u>11</u>	<u>* 8 5/8</u>	<u>32 #</u>		<u>4200</u>	<u>2800 Circ</u>
<u>7 7/8</u>	<u>* 5 1/2</u>	<u>17 # + 15.5 #</u>		<u>TD 8200</u>	<u>800 SX As Warranted</u>

Casing Data:

Surface joints of 13 3/8 inch 54.5 # Grade K-55

(Approved) (Rejected)

Inspected by MCS date Dec-92

Cementing Program

Size of hole 17 1/2 Size of Casing 13 3/8 Sacks cement required Type of Shoe used guide Float collar used yes Btm 3 jts welded yesTD of hole 504' Set 504' Feet of 13 3/8 inch 54.5 # Grade K-55(New) used csg. @ 504' with 225 27cc sacks neat cement around shoe
+ 250 sax C additives 1/4" celoseal, 270 ccPlug down @ 6:30 (AM) (PM) Date Dec 3 92Cement circulated yes No. of Sacks 95 SXCemented by Western Company Witnessed by Mike StubblefieldTemp. Survey ran @ (AM) (PM) Date top cement @ Casing test @ (AM) (PM) Date Method Used Witnessed by Checked for shut off @ (AM) (PM) Date Method used Witnessed by Remarks: