

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Yates Petr. Corp.</u>		Lease <u>Pauline ALB St.</u>		Well # <u>2</u>	
Location of Well	Unit <u>P</u>	Section <u>32</u>	Township <u>23</u>	Range <u>31</u>	County <u>Eddy</u>
Drilling Contractor	<u>Undesignated</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>- 13 3/8</u>	<u>54.5 #</u>		<u>500</u>	<u>700 Circ</u>
<u>11</u>	<u>- 8 5/8</u>	<u>32 #</u>		<u>4200</u>	<u>2900 Circ</u>
<u>7 7/8</u>	<u>- 5 1/2</u>	<u>17 # + 15.5 #</u>		<u>TD 8200</u>	<u>800 5x As Warranted</u>

Casing Data:

Surface 99 joints of 8 5/8 inch 32 # Grade J55
 (Approved) (Rejected)

Inspected by _____ date _____

Cementing Program

Size of hole 11 Size of Casing 8 5/8 Sacks cement required 1975 5x2

Type of Shoe used Tex Float collar used Yes Btm 3 jts welded Yes

TD of hole 4041 Set 4140 Feet of 8 5/8 Inch 32 # Grade J55

New used csg. @ 4140 with 200 sacks neat cement around shoe
 + 1775 sax Pacesetter Lite additives 10# salt 14# celcelc

Plug down @ 2:15 (AM) (PM) Date 2-5-93

Cement circulated Yes No. of Sacks 225

Cemented by Western Co Witnessed by JR

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks:

Dr/g. break @ 3805