

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Bass Enterprises Prod Co.</u>		Lease <u>James Ranch Unit</u>		Well # <u>29</u>	
Location of Well	Unit <u>K</u>	Section <u>36</u>	Township <u>22</u>	Range <u>30</u>	County <u>Eddy</u>
Drilling Contractor	<u>NA</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

* Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	* <u>13 3/8</u>	<u>42 #</u>		<u>550</u>	<u>360 Surf</u>
<u>11</u>	* <u>8 5/8</u>	<u>32 #</u>		<u>3800</u>	<u>980 Surf</u>
<u>7 7/8</u>	<u>5 1/2</u>	<u>15.5 #</u>		<u>8000</u>	<u>600</u>

Casing Data:

Surface joints of 8 5/8" inch 32 # Grade W.C. - 50

(Approved) (Rejected)

Inspected by M.S. date JAN. 20-94

Cementing Program

Size of hole 11" Size of Casing 8 5/8" Sacks cement required

Type of Shoe used float Float coliar used yes Btm 3 jts welded yes

TD of hole 3764' Set 3764' Feet of 8 5/8" Inch 32 # Grade W.C. - 50

New-used csg. @ 3764' with 225 sacks neat cement around shoe

+ 970 sax Pacesetter Lite - C additives 5# SALT, 1/4# celluscal,

Plug down @ 6:00 (AM) (PM) Date JAN. 22-94

Cement circulated yes No. of Sacks 232 sx

Cemented by Western Company Witnessed by Mike Stubblefield

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks:

6 centralizer every third B. SALT - 3606'