

## FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

30-015-2842

|                                               |                  |                                       |                                    |                    |                       |
|-----------------------------------------------|------------------|---------------------------------------|------------------------------------|--------------------|-----------------------|
| Operator<br><u>Tetaco Expl &amp; Prod Inc</u> |                  | Lease<br><u>Remuda Basin "19" St.</u> |                                    | Well #<br><u>4</u> |                       |
| Location of Well                              | Unit<br><u>N</u> | Section<br><u>19</u>                  | Township<br><u>23</u>              | Range<br><u>30</u> | County<br><u>Eddy</u> |
| Drilling Contractor                           | <u>N.A.</u>      |                                       | Type of Equipment<br><u>Rotary</u> |                    |                       |

## APPROVED CASING PROGRAM

| Size of Hole  | Size of Casing | Weight Per Foot | New or Used | Depth        | Sacks Ceme       |
|---------------|----------------|-----------------|-------------|--------------|------------------|
| <u>14 3/4</u> | <u>11 3/4</u>  | <u>42 #</u>     |             | <u>400'</u>  | <u>250 Surf</u>  |
| <u>11</u>     | <u>8 5/8</u>   | <u>24 #</u>     |             | <u>3200'</u> | <u>850 Surf</u>  |
| <u>7 7/8</u>  | <u>5 1/2</u>   | <u>15.5 #</u>   |             | <u>7500'</u> | <u>1650 Surf</u> |

## Casing Data:

Surface 10 joints of 11 3/4 inch 42 # Grade WC-40

(Approved) (Rejected)

Inspected by Mike Studdert date 7/21/95

## Cementing Program

Size of hole 14 3/4 Size of Casing 11 3/4 Sacks cement requiredType of Shoe used Guide Float collar used Btm 3 jts welded YesTD of hole 405 Set 420 Feet of 11 3/4 Inch 42 # Grade WC-40New-used csg. @ 400 with 400 sacks neat cement around shoe  
+ 2 sack additives 27 ccPlug down @ 4:30 (AM) (PM) Date 7/22/95Cement circulated Yes No. of Sacks 200 sacks to pitCemented by Danell Schlemmer Witnessed by Gary Williams

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: 3- cont.