

FH "28" STATE COM, WELL NO. 2

Page 2

Cement first stage w/330 sx. of Halad Light + 1/4# flocele/sx. Tail in with 300 sx. 50/50 POZ + 3% salt + 2% CaCl. Second stage cmt, w/455 sx. Halco Light + 5% salt = 1/4# flocele/sx.

4. Run 4 1/2" liner from 10,700' to 12,000'. Cement with 100 sx. Class "H" cement - circulated.