

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

30-015-30829

Operator <u>Bass Enterprises Prod.</u>		Lease <u>James Ranch Ut</u>		Well # <u>31</u>	
Location of Well	Unit <u>G</u>	Section <u>36</u>	Township <u>22</u>	Range <u>30</u>	County <u>Eddy</u>
Drilling Contractor <u>WEK Rig. 1</u>	Type of Equipment <u>Rotary</u>				
OPERATOR TO FOLLOW <u>R-111-P</u>					Expires <u>11-10-00</u>
APPROVED CASING PROGRAM					
* Witness <u>13 3/8 + 8 5/8</u> W.O.C. <u>24 Hours</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>* 13 3/8</u>	<u>48#</u>	<u>WITNESSED 12/10/99</u>	<u>580'</u>	<u>470 Surf</u>
<u>11</u>	<u>* 8 5/8</u>	<u>28# + 32#</u>		<u>3840'</u>	<u>860 Surf</u>
<u>7 7/8</u>	<u>5 1/2</u>	<u>15.5 + 17#</u>		<u>8000'</u>	<u>585 3540'</u>
Casing Data:					
Surface <u>89</u> joints of <u>8 5/8</u> inch <u>28/32</u> = Grade <u>w/c 50</u>					
(Approved) (Rejected) <u>peny/peny</u>					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>11</u> Size of Casing <u>8 5/8</u> Sacks cement required <u>850</u>					
Type of Shoe used _____ Float collar used _____ Btm 3 jts welded _____					
TD of hole <u>3840</u> Set <u>3837</u> Feet of <u>8 5/8</u> Inch <u>28/32</u> = Grade _____					
New-used csg. @ _____ with <u>190</u> sacks neat cement around shoe					
+ <u>800</u> sax <u>50/50 Poz C</u> additives <u>10% gel 5# Salt 1/4# Cellof lake</u>					
Plug down @ <u>5:30</u> (AM) (PM) Date <u>12-16-99</u>					
Cement circulated <u>50/50 Poz C</u> No. of Sacks <u>284</u>					
Cemented by <u>B.G. Hughes</u> Witnessed by <u>peny/peny</u>					
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: _____					