

PAGE START DATE: 6/22/97  
PAGE START TIME: 0: 0: 0  
DATA FILE: 3

| DELTA TIME<br>HRS | DEPTH<br>FEET | TEMPERATURE<br>'F | COMMENTS |
|-------------------|---------------|-------------------|----------|
| 0.000             | 2000.00       | 90.00             |          |
| 0.633             | 4220.00       | 97.75             |          |
| 0.650             | 4281.00       | 112.00            | BREAK    |
| 0.667             | 4350.00       | 111.00            |          |
| 0.683             | 4421.00       | 116.50            |          |
| 0.700             | 4492.00       | 112.50            |          |
| 0.708             | 4528.00       | 113.50            |          |
| 0.733             | 4637.00       | 113.00            |          |
| 0.783             | 4865.00       | 138.25            |          |
| 0.792             | 4903.00       | 121.50            |          |
| 0.817             | 4956.00       | 136.00            | M.D.R.   |

DATE AND TIME CEMENT JOB COMPLETE:

JUNE 21, 1997 @ 1:25 PM

DATE AND TIME SURVEY MADE:

JUNE 22, 1997 @ 12:05 A.M.

AMOUNT AND TYPE CEMENT USED:

100 SACKS 35:65 POSMIX, 6% GEL, 1/4#  
CELOFLAKE; 200 SACKS CLASS "C" NEAT  
RUN THROUGH D.V. TOOL AT 5014 FEET  
BEHIND 5 1/2" CASING IN A 7-7/8" HOLE.

DEPTH FIGURED FROM:

KELLY BUSHING