

PAGE START DATE: 6/12/97
PAGE START TIME: 1:52: 0
DATA FILE: 3

DELTA TIME HRS	DEPTH FEET	TEMPERATURE 'F	COMMENTS
0.000	20.00	85.00	
0.733	1360.00	92.50	
0.783	1562.00	137.00	BREAK
0.817	1693.00	126.75	
0.833	1768.00	130.00	
0.842	1798.00	121.50	
0.858	1864.00	123.75	
0.892	2008.00	114.75	
0.925	2160.00	132.50	
0.942	2238.00	125.50	
0.992	2476.00	149.25	
1.008	2545.00	140.00	
1.017	2583.00	142.50	
1.050	2736.00	115.25	
1.067	2817.00	125.25	
1.117	3045.00	114.00	
1.142	3163.00	128.00	
1.208	3469.00	112.75	
1.250	3650.00	133.50	
1.267	3728.00	113.25	
1.317	3896.00	134.25	M.D.R.

DATE AND TIME CEMENT JOB COMPLETE:

JUNE 11, 1997 @ 6:58 PM

DATE AND TIME SURVEY MADE:

JUNE 12, 1997 @ 2:30 AM

AMOUNT AND TYPE CEMENT USED:

1400 SACKS 35:65 POSMIX WITH
ADDITIVES AND 150 SACKS CALSS C
NEAT RUN BEHIND 4070 FEET OF 8-5/8"
CASING IN AN 11" HOLE.

DEPTH FIGURED FROM:

KELLY BUSHING