UNITED STATES DEPARTMENT OF THE INTERIOR **BUREAU OF LAND MANAGEMENT**

SUNDRY NOTICES AND REPORTS ON WELLS

FORM APPROVED	
OM B No. 1004-0137	
Exnires: March 31, 200	١

5.	Lease Serial No.
	SF_078508

 f Indian	Allottee or Tribe	Noma

	rell. Use Form 3160 - 3			5 NA	,,
SUBMIT IN TR	IPLICATE- Other ins	tructions on rever	se side REUENVED	7. If Unit o	r CA/Agreement, Name and/or No.
	Gas Well Other	210	BLH FARMINGTON:	8. Well Na	me and No.
2. Name of Operator Koch Explor	ation Company, LLC			9. API W	
3a. Address PO Box 489, Aztec, NM 87410		3b. Phone No. (include area code) 505-334-9111		30-045-32629 10. Field and Pool, or Exploratory Area Basin Fruitland Coal	
4. Location of Well (Footage, Sec., T., R., M., or Survey Description)					
1860' FNL & 1345' FWL, S13, T31N, R9W "F" Lat 36.53.597, Long 107.44.103			11. County or Parish, State San Juan, New Mexico		
12. CHECK A	PPROPRIATE BOX(ES) TO	O INDICATE NATUR	E OF NOTICE, R	EPORT, O	R OTHER DATA
TYPE OF SUBMISSION	TYPE OF ACTION				
Notice of Intent Subsequent Report	Acidize Alter Casing Casing Repair	Deepen Fracture Treat New Construction	Production (Sta	rt/Resume)	Water Shut-Off Well Integrity Other Intermediate
	Change Plans	Plug and Abandon	Temporarily Abandon		Casing and cement
Final Abandonment Notice	Convert to Injection Plug Back Water Disposal				
If the proposal is to deepen dire	ectionally or recomplete horizonta	lly, give subsurface location	is and measured and tru	e vertical dept	ork and approximate duration thereof. hs of all pertinent markers and zones. reports shall be filed within 30 days

determined that the site is ready for final inspection.) 05/19-20/07 Drilled 8 3/4" hole to 2952', ran 7", 23#, J-55 LTC casing, landed @ 2949'. Pump lead cement 383 sks Premium Lite FM cement, plus 3% CaCl, plus 0.25 lb/sk Celloflake, plus 5 lb/sk LCM-1, plus 0.4% FL-52A, plus 8% Bentonite, plus 0.4% Sodium Metasilicate, yield 2.13 (12.1 ppg), 815.79 cu.ft. Tail cement 84 sks Type III cement plus 1% CaCl, plus 0.25 lb/sk Celloflake, plus 0.2% FL-52, yield 1.38 (14.6 ppg), 115.92 cu. ft. We used centralizers every other joint above the shoe to the turbolizers. Ran I turbolizer at the base of the Ojo, and I turbolizer 1 joint up in the Ojo. Then centralizers every 400' to the surface pipe. Circulated 20 bbls of cement to surface. Wait on cement 8 hours. 5/20/07 tagged cement @ 2903'. Pressure Tested 7" casing to 1500# for 30 minutes, held O.K. Tested BOPS to 250# low for 5 minutes, and 2000# high

following completion of the involved operations. If the operation results in a multiple completion or recompletion in a new interval, a Form 3160-4 shall be filed once testing has been completed. Final Abandonment Notices shall be filed only after all requirements, including reclamation, have been completed, and the operator has





