

ATTACHMENT TO J. FELIX HICKMAN, SCHMITZ 2 (N.M. 03556)

Cementing record for 7" casing:

stage 1-335 ft.³ 50-50 Poz. + 2% gel + 6½# Gilsonite + ½# Flocele + 9# salt/sk.

stage tool at 3898'

cement top stage 1 = 4000'

stage 2 - 345 ft.³ 65-35 Poz. + 12% gel. followed by 59 ft.³ Class B

cement top stage 2 = 2000'