

UNITED STATES  
DEPARTMENT OF THE INTERIOR  
GEOLOGICAL SURVEY

## SUNDRY NOTICES AND REPORTS ON WELLS

(Do not use this form for proposals to drill or to deepen or plug back to a different reservoir. Use Form 9-331-C for such proposals.)

1. oil ☐ gas ☒ other2. NAME OF OPERATOR  
Jerome P. McHugh3. ADDRESS OF OPERATOR  
Box 208, Farmington, NM 87401

4. LOCATION OF WELL (REPORT LOCATION CLEARLY. See space 17 below.)

AT SURFACE: 1850' FNL - 1450' FEL

AT TOP PROD. INTERVAL:

AT TOTAL DEPTH:

16. CHECK APPROPRIATE BOX TO INDICATE NATURE OF NOTICE, REPORT, OR OTHER DATA

REQUEST FOR APPROVAL TO:

SUBSEQUENT REPORT OF:

TEST WATER SHUT-OFF ☐FRACTURE TREAT ☐SHOOT OR ACIDIZE ☐REPAIR WELL ☐PULL OR ALTER CASING ☐MULTIPLE COMPLETE ☐CHANGE ZONES ☐ABANDON\* ☐(other) csg and cement job

(NOTE: Report results of multiple completion or zone change on Form 9-330.)

17. DESCRIBE PROPOSED OR COMPLETED OPERATIONS (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work. If well is directionally drilled, give subsurface locations and measured and true vertical depths for all markers and zones pertinent to this work.)\*

COMPLETE REPORT ON BACK

RECEIVED

NOV 20 1979

U. S. GEOLOGICAL SURVEY  
FARMINGTON, N. M.

Subsurface Safety Valve: Manu. and Type \_\_\_\_\_

18. I hereby certify that the foregoing is true and correct

SIGNED

Jim L. Jacobs

TITLE

Agent

DATE

11-16-79

Set @

Ft.

APPROVED BY

CONDITIONS OF APPROVAL, IF ANY:

TITLE

DATE

11-14-79

Ran 199 jts 4-1/2" OD 11.6# & 10.5# 8R ST&C Lone Star csg. TE 7802.82' set @ 7785' RKB. Cemented 1st stage w/400 gal. chemical wash followed by 200 sx class "B" 8% gel and 150 sx class "B" w/7-1/2# salt per sx (total slurry 555 cu ft) Reciprocated pipe OK while cementing. Had full mud returns throughout job. PD first stage @ 5:50 p.m. 11-13-79. Opened Baker stage tool @ 5674'. Circulated w/rig pump for 3 hrs. Circulated out undetermined amount of cement.

Cemented second stage with 400 gal chemical wash, 250 sx 65-35 plus 12% gel and 1/4# cellophane flakes per sx (total slurry 714 cu ft). Had good mud returns throughout job. Opened Baker stage tool @ 3486'. Circulated w/rig pump 2-3/4 hrs.

Cemented third stage as follows: 400 gals chemical wash, 375 sx 65-35 plus 12% gel and 1/4# cellophane flakes per sx followed by 50 sx class "B" w/1/4# cellophane flakes per sx. (total slurry 1041 cu ft). Circulated out approximately 5 bbls cement. Job complete 1:25 a.m. 11-14-79. Released rig @ 3:00 a.m. 11-14-79