


(SUBMIT IN TRIPLICATE)

UNITED STATES  
DEPARTMENT OF THE INTERIOR  
GEOLOGICAL SURVEY

Land Office New Mexico  
Lease No. 03380  
Unit Florance



SUNDRY NOTICES AND REPORTS ON WELLS

NOTICE OF INTENTION TO DRILL	SUBSEQUENT REPORT OF WATER SHUT-OFF
NOTICE OF INTENTION TO CHANGE PLANS	SUBSEQUENT REPORT OF SHOOTING OR ACIDIZING
NOTICE OF INTENTION TO TEST WATER SHUT-OFF	SUBSEQUENT REPORT OF ALTERING CASING
NOTICE OF INTENTION TO RE-DRILL OR REPAIR WELL	SUBSEQUENT REPORT OF RE-DRILLING OR REPAIR
NOTICE OF INTENTION TO SHOOT OR ACIDIZE	SUBSEQUENT REPORT OF ABANDONMENT
NOTICE OF INTENTION TO PULL OR ALTER CASING	SUPPLEMENTARY WELL HISTORY
NOTICE OF INTENTION TO ABANDON WELL	

(INDICATE ABOVE BY CHECK MARK NATURE OF REPORT, NOTICE, OR OTHER DATA)

March 28, 1950

Well No. 10-B is located 790 ft. from N line and 1650 ft. from E line of sec. 17

17 Sec. 17 27N 3W T.M.P.M.  
( $\frac{1}{4}$  Sec. and Sec. No.) (Twp.) (Range) (Meridian)  
Blanco, N.Y. Co. Blanco, P.C. San Juan New Mexico  
(Field) (County or Subdivision) (State or Territory)

The elevation of the derrick floor above sea level is 6732 ft.

DETAILS OF WORK


(State names of and expected depths to objective sands; show sizes, weights, and lengths of proposed casings; indicate mudding jobs, cementing points, and all other important proposed work)

2-3-58. Total Depth 5346'.

Ran 11 joints 5 1/2", 15.50#, J-55 Liner (426') set from 4914 to 5340' with 25 sacks regular cement, 25 sacks Pozzix, 6# Gel, 1/8# Floccle/sk, followed by 50 sacks regular cement.

Held 1000# for 30 minutes.

Top of cement by temperature survey at 4914'.



I understand that this plan of work must receive approval in writing by the Geological Survey before operations may be commenced.

Company El Paso Natural Gas Company

Address Box 217

Farmington, New Mexico

By Original Signed D. C. Johnson

Title Petroleum Engineer

# B. & R. SERVICE COMPANY

## TEMPERATURE SURVEY

COMPANY EL PASO NATURAL GAS COMPANY

WELL FLORENCE 10-D

FIELD

COUNTY SAN JUAN

STATE NEW MEXICO

SEC. 17

TWP.

27

RGE. 8

APPROX. TOP CEMENT 4000'

Survey Begins at 3500' Ft. Ends at 4883' Ft.

Approx. Fill-Up 75% Max. Temp. 133° @ 4883'

Log Measured From ROTARY TABLE Run No. 1

Casing Size

Casing Depth

Diam of Hole

Depth

7 5/8" from 0

to 4964'

9 5/8" from

to

from

to

from

to

Date of Cementing MARCH 1, 1958

Time 5:00 A.M.

Date of Survey MARCH 1, 1958

Time 5:00 P.M.

Amount of Cement 250 SACKS

Type 50/50 PCZMIX

Amount of Admix 2% GEL

Type

Recorded by L.R. ELKIN

Witnessed by HEARD

REMARKS OR OTHER DATA


RECEIVED

MAR 6 1958

OIL CON. COM.

DIST. 3

## TEMPERATURE IN DEGREES FAHRENHEIT



# B. & R. SERVICE COMPANY

## TEMPERATURE SURVEY

COMPANY EL PASO NATURAL GAS COMPANY  
 WELL FLORENCE 10-D FIELD   
 COUNTY SAN JUAN STATE NEW MEXICO  
 SEC. 17 TWP. 27 RGE. 8

APPROX. TOP CEMENT 2550'

Survey Begins at 2000 Ft. Ends at 3012 Ft.  
 Approx. Fill-Up  Max. Temp. 114° @ 3012'  
 Log Measured From RIG FLOOR Run No. 1


Casing Size	Casing Depth	Diam of Hole	Depth
7 $\frac{5}{8}$ " from <u>0</u> to <u></u>		9 $\frac{5}{8}$ " from <u></u> to <u></u>	
from <u></u> to <u></u>		from <u></u> to <u></u>	

Date of Cementing MARCH 6, 1958 Time 9:30 A.M.  
 Date of Survey MARCH 6, 1958 Time 1:00 P.M.  
 Amount of Cement 250 SACKS Type REGULAR  
 Amount of Admix 2% GEL Type   
 Recorded by C. GLASSER Witnessed by J. GAY

### REMARKS OR OTHER DATA

7 $\frac{5}{8}$ " PIPE SQUEEZED AT 3100'

### TEMPERATURE IN DEGREES FAHRENHEIT



B. & R.  
SERVICE COMPANY

TEMPERATURE SURVEY

COMPANY.....EL PASO NATURAL GAS COMPANY  
WELL FLORENCE # 10-D.....FIELD.....  
COUNTY SAN JUAN.....STATE NEW MEXICO  
SEC. 17.....TWP. 27.....RGE. 8

APPROX. TOP CEMENT.....4914'

Survey Begins at 4000.....Ft. Ends at 5204.....Ft.  
Approx. Fill-Up.....Max. Temp. 132° @ 5204'  
Log Measured From ROTARY TABLE Run No. 1

Casing Size	Casing Depth	Diam of Hole	Depth
5½" from 0	to 5340'	6¾" from	to
from	to	from	to

Date of Cementing MARCH 3, 1958.....Time 5:30 P.M.  
Date of Survey MARCH 4, 1958.....Time 5:30 A.M.  
Amount of Cement 50 SACKS.....Type 50/50 POZMIX  
Amount of Admix 6% GEL.....Type.....  
Recorded by M. CAPPS.....Witnessed by ANDERSON

REMARKS OR OTHER DATA

TOP OF LINER AT 4914'

TEMPERATURE IN DEGREES FAHRENHEIT

