

✱

Cementing - 8-5/8"

Cemented from top w/25 sks "B" + 4% CaCl_2 .

Cementing - 4-1/2" 1st stage - 465 sx Class

"B" w/10% salt - 2nd stage @ 4,363' 610 sks

of 50-50 Pozmix w/2% gel + 1/4#/sk Flocele.

3rd stage @ 1,829' 375 sx of 65-35 Pozmix

w/6% gel followed by 385 sx 50-50 Pozmix

w/2% gel + 1/4#/sk Flocele.