

Angel Peak "B" 37
Section 24, T-28N, R-11W
San Juan County, New Mexico

Item 28: Cement Record

Cemented 9-5/8" with 295 cu.ft. C1 B w/2% CaCl_2 .

Cemented 7" 1st stage with 1435 cu.ft. 65-35 POZ w/12% Gel, 12-1/4# Gilsonite, and 1/4# Flocele per sack followed by 118 cu.ft. C1 B w/2% CaCl_2 . Cemented 2nd stage with 904 cu.ft. 65-35 POZ w/12% Gel, 12-1/4# Gilsonite and 1/4# Flocele per sack followed by 118 cu.ft. C1 B w/2% CaCl_2 .

Cemented 4-1/2" with 175 cu.ft. C1 B w/2% Gel, 0.6% FLA, 1/4# Flocele and 10# salt per sack.

Item 32: Stimulation Record

Perfs	6160'-6231'	Breakdown and acidize with 500 gallons 15% HCl. Fracture with 27,456 gallons of 40# Gel and 1600# sand.
Perfs	5854'-6004'	Breakdown and acidize with 1250 gallons 15% HCl. Fracture with 65,000 gallosn of 70 quality foam 13,600# sand.
Perfs	5433'-5780'	Breakdown and acidize with 2000 gallons 15% HCl. Fracture with 186,340 gallons 70 quality foam and 179,500# sand.