

S. & R.
SALES & SERVICE

TEMPERATURE SURVEY

COMPANY.....El Paso Natural Gas Co.
WELL.....4-A.....LEASE.....Barrett
COUNTY.....San Juan.....STATE.....New Mexico
SEC. P.....20.....TWP.....31.....RGE.....9

APPROX. TOP CEMENT.....1680'

Survey Begins at 1000'.....Ft. Ends at 3413'.....Ft.
Approx. Fill-Up.....Max. Temp.....
Log Measured From K-B.....Run No. 1

Casing Size	Casing Depth	Diam of Hole	Depth
7" from	to 8 3/4"	from	to
from	to	from	to

Date of Cementing.....8/21/77.....Time 11:15AM
Date of Survey.....8/21/77.....Time 7:00PM
Amount of Cement 105 Scks 65/35 Class B Poz w 12% Gel & 1/2 Cu.Ft.
Fine Gilsomite per Sck & 100 Scks Class B with 2% Ca.Cl. & 1/2 Cu. Ft.

Recorded by Hunter.....Witnessed by.....Fine Gilsomite per sck.

REMARKS OR OTHER DATA
Latch down Baffle set @ 3435

TEMPERATURE IN DEGREES FAHRENHEIT

