

UNITED STATES
DEPARTMENT OF THE INTERIOR
BUREAU OF LAND MANAGEMENT

Sundry Notices and Reports on Wells

1. Type of Well
GAS

2. Name of Operator

**BURLINGTON
RESOURCES**

OIL & GAS COMPANY

3. Address & Phone No. of Operator

PO Box 4289, Farmington, NM 87499 (505) 326-9700

4. Location of Well, Footage, Sec., T, R, M

1797' FNL, 1085' FEL, Sec.25, T-31-N, R-9-W, NMPM

5. Lease Number
SF-078505

6. If Indian, All. or
Tribe Name

7. Unit Agreement Name

8. Well Name & Number
Seymour #1B

9. API Well No.
30-045-30021

10. Field and Pool
Blanco MV/Basin DK

11. County and State
San Juan Co, NM

12. CHECK APPROPRIATE BOX TO INDICATE NATURE OF NOTICE, REPORT, OTHER DATA

Type of Submission

☒ Notice of Intent
☐ Subsequent Report
☐ Final Abandonment

Type of Action

☐ Abandonment
☐ Recompletion
☐ Plugging Back
☐ Casing Repair
☒ Altering Casing
☐ Other -
☒ Change of Plans
☐ New Construction
☐ Non-Routine Fracturing
☐ Water Shut off
☐ Conversion to Injection

13. Describe Proposed or Completed Operations

It is intended to alter the approved casing depths and cement of the subject well:

Revisions:

Mud Program:

Interval	Type	Weight	Fluid Loss
0-200'	Spud	8.4-9.0	No Control
200-3499'	LSND	8.4-9.0	No Control
3499-8000'	Air/Mist	n/a	n/a

Casing Program:

Hole Size	Depth Interval	Casing Size	Weight
17-1/2"	0-200'	13-3/8"	48#
10-5/8"	0-3499'	8-5/8"	32#
7-7/8"	3399-8000'	5-1/2"	15.50#
Tubing Program:	0-5825'	1-1/2"	2.75# IJ
	0-8000'	1-1/2"	2.90# EUE

Cementing Program:

13-3/8" surface casing - 353 sx Class "B" cement with 0.25 pps flocele and 3% calcium chloride (1477 cu.ft. of slurry, 200% excess to circulate to surface).
8-5/8" intermediate casing - Lead with 452 sx Class "B" cement with 3% sodium metasilicate, 5 pps Gilsonite, 0.25 pps flocele. Tail with 90 sx Class "B" cement with 2% sodium metasilicate, 2% calcium chloride, 5 pps Gilsonite and 0.25 pps flocele (1470 cu.ft. of slurry, 100% excess to circulate to surface).
8-5/8" intermediate casing (alternative two stage cement job) - 1st Stage with 220 sx Class "B" cement with 2% sodium metasilicate, 2% calcium chloride, 5 pps Gilsonite and 0.25 pps flocele. 2nd Stage with 375 sx Class "B" cement with 3% sodium metasilicate, 5 pps Gilsonite, 0.25 pps flocele. Stage tool at 2600'. (1470 cu.ft. of slurry, 100% excess to circulate to surface).
5-1/2" production liner - 866 sx Class "B" 50/50 poz with 2% gel, 0.25 pps flocele, 5 pps gilsonite, 0.4% fluid loss, 0.1% retardant (1117 cu.ft. of slurry, 40% excess to circulate to top of liner).

Wellhead:

13-3/8" x 8-5/8" x 1-1/2" EUE x 1-1/2" IJ x 5000 psi tree assembly.

14. I hereby certify that the foregoing is true and correct.

Signed Regan Cole (DWS) Title Regulatory Administrator Date 1/26/00
no

(This space for Federal or State Office use)

APPROVED BY /s/ Charlie Beecham Title Team Lead, Petroleum Management Date MAR 14 2000

CONDITION OF APPROVAL, if any: