

**B. & R.
SERVICE COMPANY**

TEMPERATURE SURVEY

COMPANY.....EL PASO NATURAL GAS COMPANY.....

WELL.....ALLISON UNIT # 16.....FIELD.....

COUNTY.....SAN JUAN.....STATE.....NEW MEXICO.....

SEC.....15.....TWP.....32.....RGE.....7.....

APPROX. TOP CEMENT.....2900'.....

Survey Begins at.....2500.....Ft. Ends at.....3832.....Ft.

Approx. Fill-Up.....68%.....Max. Temp.....109° @ 3832'

Log Measured From.....R.T.A.....Run No.....ONE.....

Casing Size	Casing Depth	Diam of Hole	Depth
9 $\frac{5}{8}$ " from	0 to 3859'	12 $\frac{1}{2}$ " from	to
from	to	from	to

Date of Cementing.....MAY 25, 1958.....Time.....12: A.M.


Date of Survey.....MAY 27, 1958.....Time.....9: A.M.

Amount of Cement.....400 SACKS.....Type.....POZMIX & REG.


Amount of Admix 4% GEL, $\frac{1}{2}$ FLOCELE.....Type.....

Recorded by.....ELKINS & WILSON.....Witnessed by.....E. P. HURBARFF.....

REMARKS OR OTHER DATA



TEMPERATURE IN DEGREES FAHRENHEIT



B. & R. SERVICE COMPANY

TEMPERATURE SURVEY

COMPANY EL PASO NATURAL GAS COMPANY
WELL ALLISON UNIT # 16 FIELD _____
COUNTY SAN JUAN STATE NEW MEXICO
SEC. 15 TWP. 32 RGE. 7

APPROX. TOP CEMENT 2800'


Survey Begins at 2000 Ft. Ends at 4141 Ft.
Approx. Fill-Up _____ Max. Temp. 120° @ 4141'
Log Measured From R.T. Run No. ONE

Casing Size	Casing Depth	Diam of Hole	Depth
<u>5½"</u> from <u>0</u> to <u>8488'</u>		<u>8½"</u> from _____ to _____	
from _____ to _____		from _____ to _____	

Date of Cementing JUNE 17, 1958 Time 7:00 A.M.
Date of Survey JUNE 17, 1958 Time 2:00 P.M.
Amount of Cement 1490 SACKS Type POZMIX & NEAT
Amount of Admix 1# FLOCELE PER SK. Type _____
Recorded by S. WILSON Witnessed by DRILLER

REMARKS OR OTHER DATA

HCLE BRIDGED OFF AND LEFT APPROXIMATELY 1200' OF
CEMENT IN CASING.



TEMPERATURE IN DEGREES FAHRENHEIT

