

30-025-44757

HOBBS OCD
SEP 10 2018
RECEIVED**Revised Permit Information 9/6/18:**

Well Name: Diamond 31 Fed Com No. 701H

Location:

SL: 618' FSL & 625' FWL, Section 31, T-24-S, R-34-E, Lea Co., N.M.

BHL: 2539' FSL & 330' FWL, Section 30, T-24-S, R-34-E, Lea Co., N.M.

Casing Program:

Hole Size	Interval	Csg OD	Weight	Grade	Conn	DF _{min} Collapse	DF _{min} Burst	DF _{min} Tension
17.5"	0 - 1,225'	13.375"	54.5#	J55	STC	1.125	1.25	1.60
12.25"	0-4,100'	9.625"	40#	J55	LTC	1.125	1.25	1.60
12.25"	4,100' - 5,100'	9.625"	40#	HCK55	LTC	1.125	1.25	1.60
8.75"	0 - 11,500'	7.625"	29.7#	HCP110	FXL	1.125	1.25	1.60
6.75"	0 - 11,000'	5.5"	20#	P110EC	DWC CIS MS	1.125	1.25	1.60
6.75"	11,000'-20,035'	5.5"	20#	P110EC	VAM SFC	1.125	1.25	1.60

Variance is requested for annular clearance of the 5-1/2" x 7-5/8" to the top of cement.

Cement Program:

Depth	No. Sacks	Wt. lb/gal	Yld Ft ³ /ft	Slurry Description
1,225'	697	13.5	1.74	Lead: Class 'C' + 4.00% Bentonite + 2.00% CaCl ₂ (TOC @ Surface)
	333	14.8	1.35	Tail: Class 'C' + 0.6% FL-62 + 0.25 lb/sk Cello-Flake + 0.2% Sodium Metasilicate + 2.0% KCl (1.06 lb/sk)
5,100'	692	12.7	2.22	Lead: Class C + 0.15% C-20 + 11.63 pps Salt + 0.1% C-51 + 0.75% C-41P (TOC @ Surface)
	303	14.8	1.32	Tail: Class C + 0.13% C-20
11,500'	375	10.8	3.67	Lead: Class C + 0.40% D013 + 0.20% D046 + 0.10% D065 + 0.20% D167 (TOC @ 4,600')
	400	14.8	2.38	Tail: Class H + 94.0 pps D909 + 0.25% D065 + 0.30% D167 + 0.02% D208 + 0.15% D800
20,035'	1000	14.8	1.31	Class H + 0.1% C-20 + 0.05% CSA-1000 + 0.20% C-49 + 0.40% C-17 (TOC @ 11,000')

Mud Program:

Depth	Type	Weight (ppg)	Viscosity	Water Loss
0 - 1225'	Fresh - Gel	8.6-8.8	28-34	N/c
1225' - 5,100'	Brine	10.0-10.2	28-34	N/c
5,100' - 11,500'	Oil Base	8.7-9.4	58-68	N/c - 6
11,500' - 20,035' Lateral	Oil Base	10.0-11.5	58-68	3 - 6

Revised Permit Information 9/6/18:

Well Name: Diamond 31 Fed Com No. 701H

Location:

SL: 618' FSL & 625' FWL, Section 31, T-24-S, R-34-E, Lea Co., N.M.

BHL: 2539' FSL & 330' FWL, Section 30, T-24-S, R-34-E, Lea Co., N.M.

Casing Program:

Hole Size	Interval	Csg OD	Weight	Grade	Conn	DF _{min} Collapse	DF _{min} Burst	DF _{min} Tension
17.5"	0 - 1,225'	13.375"	54.5#	J55	STC	1.125	1.25	1.60
12.25"	0-4,100'	9.625"	40#	J55	LTC	1.125	1.25	1.60
12.25"	4,100' - 5,100'	9.625"	40#	HCK55	LTC	1.125	1.25	1.60
8.75"	0 - 11,500'	7.625"	29.7#	HCP110	FXL	1.125	1.25	1.60
6.75"	0 - 11,000'	5.5"	20#	P110EC	DWC CIS MS	1.125	1.25	1.60
6.75"	11,000' - 20,035'	5.5"	20#	P110EC	VAM SFC	1.125	1.25	1.60

Variance is requested for annular clearance of the 5-1/2" x 7-5/8" to the top of cement.

Cement Program:

Depth	No. Sacks	Wt. lb/gal	Yld Ft ³ /ft	Slurry Description
1,225'	697	13.5	1.74	Lead: Class 'C' + 4.00% Bentonite + 2.00% CaCl ₂ (TOC @ Surface)
	333	14.8	1.35	Tail: Class 'C' + 0.6% FL-62 + 0.25 lb/sk Cello-Flake + 0.2% Sodium Metasilicate + 2.0% KCl (1.06 lb/sk)
5,100'	692	12.7	2.22	Lead: Class C + 0.15% C-20 + 11.63 pps Salt + 0.1% C-51 + 0.75% C-41P (TOC @ Surface)
	303	14.8	1.32	Tail: Class C + 0.13% C-20
11,500'	375	10.8	3.67	Lead: Class C + 0.40% D013 + 0.20% D046 + 0.10% D065 + 0.20% D167 (TOC @ 4,600')
	400	14.8	2.38	Tail: Class H + 94.0 pps D909 + 0.25% D065 + 0.30% D167 + 0.02% D208 + 0.15% D800
20,035'	1000	14.8	1.31	Class H + 0.1% C-20 + 0.05% CSA-1000 + 0.20% C-49 + 0.40% C-17 (TOC @ 11,000')

Mud Program:

Depth	Type	Weight (ppg)	Viscosity	Water Loss
0 - 1225'	Fresh - Gel	8.6-8.8	28-34	N/c
1225' - 5,100'	Brine	10.0-10.2	28-34	N/c
5,100' - 11,500'	Oil Base	8.7-9.4	58-68	N/c - 6
11,500' - 20,035' Lateral	Oil Base	10.0-11.5	58-68	3 - 6

Revised Permit Information 9/6/18:

Well Name: Diamond 31 Fed Com No. 701H

Location:

SL: 618' FSL & 625' FWL, Section 31, T-24-S, R-34-E, Lea Co., N.M.

BHL: 2539' FSL & 330' FWL, Section 30, T-24-S, R-34-E, Lea Co., N.M.

Casing Program:

Hole Size	Interval	Csg OD	Weight	Grade	Conn	DF _{min} Collapse	DF _{min} Burst	DF _{min} Tension
17.5"	0 - 1,225'	13.375"	54.5#	J55	STC	1.125	1.25	1.60
12.25"	0-4,100'	9.625"	40#	J55	LTC	1.125	1.25	1.60
12.25"	4,100' - 5,100'	9.625"	40#	HCK55	LTC	1.125	1.25	1.60
8.75"	0 - 11,500'	7.625"	29.7#	HCP110	FXL	1.125	1.25	1.60
6.75"	0 - 11,000'	5.5"	20#	P110EC	DWC CIS MS	1.125	1.25	1.60
6.75"	11,000' - 20,035'	5.5"	20#	P110EC	VAM SFC	1.125	1.25	1.60

Variance is requested for annular clearance of the 5-1/2" x 7-5/8" to the top of cement.

Cement Program:

Depth	No. Sacks	Wt. lb/gal	Yld Ft ³ /ft	Slurry Description
1,225'	697	13.5	1.74	Lead: Class 'C' + 4.00% Bentonite + 2.00% CaCl ₂ (TOC @ Surface)
	333	14.8	1.35	Tail: Class 'C' + 0.6% FL-62 + 0.25 lb/sk Cello-Flake + 0.2% Sodium Metasilicate + 2.0% KCl (1.06 lb/sk)
5,100'	692	12.7	2.22	Lead: Class C + 0.15% C-20 + 11.63 pps Salt + 0.1% C-51 + 0.75% C-41P (TOC @ Surface)
	303	14.8	1.32	Tail: Class C + 0.13% C-20
11,500'	375	10.8	3.67	Lead: Class C + 0.40% D013 + 0.20% D046 + 0.10% D065 + 0.20% D167 (TOC @ 4,600')
	400	14.8	2.38	Tail: Class H + 94.0 pps D909 + 0.25% D065 + 0.30% D167 + 0.02% D208 + 0.15% D800
20,035'	1000	14.8	1.31	Class H + 0.1% C-20 + 0.05% CSA-1000 + 0.20% C-49 + 0.40% C-17 (TOC @ 11,000')

Mud Program:

Depth	Type	Weight (ppg)	Viscosity	Water Loss
0 - 1225'	Fresh - Gel	8.6-8.8	28-34	N/c
1225' - 5,100'	Brine	10.0-10.2	28-34	N/c
5,100' - 11,500'	Oil Base	8.7-9.4	58-68	N/c - 6
11,500' - 20,035' Lateral	Oil Base	10.0-11.5	58-68	3 - 6