

CEMENT

<u>TYPE OF STRING INTERVAL (FT) FROM-TO TYPE MIX</u>	<u>GEL%</u>	<u>SALT%</u>	<u>CaCl2</u>	<u>SLURRY WEIGHT LB./GAL</u>	<u>SLURRY YIELD OF/SKX</u>	<u>TOTAL AMT. REQUIRED SKX/CF</u>	<u>FILL UP</u>	<u>BHT</u>	<u>SIZE</u>	<u>REMARKS</u>
(S) 0'-1600' Class 'C'	4%		2%	13.50	1.88	572/1074	circulate		12 1/4"	100% excess
Class 'C'			2%	14.80	1.32	184/248				
(P) 0'-3880' *Class 'C' Light	18%			13.20	1.92	(430) 828	circulate		7 7/8"	100% excess
Class 'C'			2%	14.80	1.32	(200) 264				

Note: Reciprocate production casing while cementing.
*Class 'C' light: Examples - BJ light, Howco light, Dowell light.
Cement volumes to be recalculated after caliper run.