

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Petroleum Corp</u>		Lease <u>Platt "PA"</u>		Well # <u>6</u>	
Location of Well	Unit <u>2310N 990W E</u>	Section <u>26</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>L + M #2</u>		Type of Equipment <u>Rotary</u> <u>10-2-81</u>		
* Witness					
APPROVED CASING PROGRAM					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>9 1/2</u>	<u>7"</u>	<u>20#</u>		<u>910'</u>	<u>525 SX Circ</u>
<u>6 1/4</u>	<u>4 1/2"</u>	<u>9.5#</u>		<u>3600</u>	<u>375 SX</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>9 1/2</u> Size of Casing <u>7"</u> Sacks cement required _____					
Type of Shoe used <u>guide</u> Float collar used <u>inst</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>920</u> Set <u>935</u> Feet of <u>7</u> Inch <u>20</u> # Grade <u>J-55</u>					
New used csg. @ <u>920</u> with <u>150</u> sacks neat cement around shoe <u>LC 3 1/2 Cask</u>					
+ <u>400</u> sax <u>Wellite</u> additives <u>3 1/2 CaCl</u> <u>(65/35)</u>					
Plug down @ <u>11:00</u> (AM) (PM) <u>(PM)</u> Date <u>10-3-81</u>					
Cement circulated <u>NO</u> No. of Sacks _____					
Cemented by <u>HALLIBURTON</u> Witnessed by <u>Larry Brock</u>					
Temp. Survey ran @ <u>6:00</u> (AM) (PM) <u>(AM)</u> Date <u>10/4/81</u> top cement @ <u>475</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>LC @ 594</u> <u>RUN 1 1/4 Tag @ 468.</u>					
<u>cent @</u> <u>Pumped</u>					
<u>Baskets @</u>					