

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Terra Resources</u>		Lease <u>Burro Canyon Unit</u>			Well # <u>1K</u>
Location of Well	Unit <u>J</u>	Section <u>2</u>	Township <u>21</u>	Range <u>20</u>	County <u>Otero</u>
Drilling Contractor	<u>Cactus</u>		Type of Equipment <u>Rotary to start 7-9-78</u>		

*Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>16</u>	<u>14</u>	<u>450#</u>		<u>40</u>	<u>Circ</u>
* <u>12 1/4</u>	<u>8 5/8</u>	<u>24#</u>		<u>1550'</u>	<u>Circ</u>
<u>7 7/8</u>	<u>4 1/2</u>	<u>11.6#</u>		<u>7800</u>	<u>450 SX</u>

Casing Data:

Surface joints of 8 5/8 inch 24 # Grade J-55
(Approved) (Rejected)

Inspected by M.S. date 7/17/78

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required 850

Type of Shoe used guide Float collar used yes Btm 3 jts welded yes

TD of hole 1607' Set 1566' Feet of 8 5/8 Inch 24 # Grade J-55

New-used csg. @ 1566' with 200 sacks neat cement around shoe

+ 650 sax Water additives 4% oil, 1/4# caloflake, 4# Kelite, 5# salt, 2% cc

Plug down @ 4:30 (AM) (PM) Date 7/22/78

Cement circulated No No. of Sacks

Cemented by Dowell Witnessed by Mike Stubblefield

Temp. Survey ran @ 11:30 (AM) (PM) Date 7/22/78 top cement @ 700'

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks:

Last day back 1310'