

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

30-015-28003

Operator <u>Nearburg Prod. Co.</u>		Lease <u>State K</u>		Well # <u>2</u>	
Location of Well	Unit <u>J</u>	Section <u>28</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor <u>Peterson Rig #4</u>	Type of Equipment <u>Rotary</u>				

APPROVED CASING PROGRAM

* Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4</u>	* <u>9 5/8</u>	<u>36 #</u>		<u>1300</u>	<u>775 Circ</u>
<u>8 3/4</u>	<u>7</u>	<u>23 # K-55</u>		<u>5000</u>	<u>950 Circ</u>
		<u>26 # K-55</u>		<u>8200</u>	

Casing Data:

Surface _____ joints of 9 5/8" inch 36 # Grade S-55

(Approved) (Rejected)

Inspected by M.S. date July 8-94

Cementing Program

Size of hole 14 3/4" Size of Casing 9 5/8" Sacks cement required _____Type of Shoe used guide Float collar used insert Btm 3 jts welded yesTD of hole 1202' Set 1202' Feet of 9 5/8" Inch 36 # Grade S-55(New)-used csg. @ 1202' with 200 2700 sacks neat cement around shoe
+ 1030 sack Hall. Lite additives 3 # SALT/SX, 1/4 # florealPlug down @ 6:45 (AM) (PM) Date July 9-94Cement circulated yes No. of Sacks 250 SXCemented by Halliburton Witnessed by Mike Stubblefield

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____

L.C. - 790' - R.M. 10yds

14 3/4" hole R.T. - 58 1/4 hrs

L.D.B. - 1030'