

Arrant, Bryan, EMNRD

From: Pat McCollom [pmccollom@rkixp.com]
Sent: Tuesday, December 04, 2007 9:29 AM
To: Arrant, Bryan, EMNRD
Cc: dkilgore@rkixp.com; GSimer@rkixp.com
Subject: Pinnacle State # 16/API #-30-015-35828 - Surface Casing Cementing Info.
Attachments: Pinnacle 16 Surface Cement Rpt.xls

Bryan,

Here is the cementing report for the well. Per our Drilling Supervisor, he was working with Mike Bradsher (ext. 108) with the NMOCD, on getting the surface casing cemented properly.

Debbie,

I spoke with Johnny Blackwood on the temperature survey. He said that a copy of the temperature survey and the Schlumberger cementing report was in a file that he turned in to Carlsbad. Perhaps you could mail a copy of the temperature survey and the Schlumberger cementing report to:

Bryan G. Arrant
District II Geologist
New Mexico Oil Conservation Division
1301 West Grand Ave.
Artesia, NM 88210
505-748-1283 Ext. 103

Thanks,

Pat

Pat McCollom
RKI Exploration & Production
Drilling & Production Engr.
Bus: 405-996-5748
Cell: 405-833-0332
Fax: 405-949-2223
pmccollom@rkixp.com

This inbound email has been scanned by the MessageLabs Email Security System.

12/9/2007

Lease: Pinnacle State #16

Date: 11/8/2007

CASING REPORT						
Ran: 11 jts.						
Csg as follows:	JTS	SIZE	WEIGHT	GRADE	THREAD	LENGTH
Top	10	9 5/8"	36.0	J-55	ST&C	424.74
F Insert						0.00
Shoe Jt.	1	9 5/8"	36.0	J-55	ST&C	42.04
Tex. Shoe					ST&C	0.50
Total						467.28
KB-CHF		KB-GND		12'	GND-ELEV	3,085'

BLM/OCD notified @ _____ Date 11/7/2007 Contact: M. Bradsher

WELLHEAD

SIZE	11"	TYPE	SOW	PSI RATING	3,000	MAKE	Wood Group
TYPE LINER HANGER @		N/A		TOP LINER	N/A	BTM LINER	N/A
CASING SHOE @		462'	FLOAT INSERT @	420'	MARKER	NA	
CENTRALIZERS: 1,2,3,4,6,8							

Cemented with: 275sx. "C" + 2% S1 + .125 pps D130 14.8 ppg. 1.34 yield, drop plug on fly bump plug w/ 1050 psi. float held did not circulate cement.

Ran temperature survey top cement @ 82', ran 1" tubing tagged @ 60', pump 25 sx. "C" 14.8 ppg. 1.34 yield. Wait 2 hrs. tagged cement 45', pumped 75 sx. 14.8 ppg. 1.34 yield, wait 2 hrs. tagged cement 35 ft, pumped 50 sx. "C" 14.8 ppg. 1.34 yield, circulated 2 bbls. To surface.

0 Sx. cement returned to surface.

Calculated top of cem. surface

Job completed @ 8:30 AM

Date: 10/11/2002

CASING				
Casing del. to location from:	Trident	Houston		
Description: 12 jts.	9 5/8"	J-55	ST&C	36#
Toolpusher's tally (threads on)	510.50			
Tally	508.55			
Company Man	J.W. Blackwood			