

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER 10  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

|                                                                       |                                                    |                                    |                       |                    |                         |
|-----------------------------------------------------------------------|----------------------------------------------------|------------------------------------|-----------------------|--------------------|-------------------------|
| Operator<br><u>Fred Pool Drilling Co</u>                              |                                                    | Lease<br><u>Hondo River Farm</u>   |                       | Well #<br><u>1</u> |                         |
| Location<br>of Well                                                   | Unit<br><small>1420W<br/>1920W</small><br><u>F</u> | Section<br><u>4</u>                | Township<br><u>11</u> | Range<br><u>25</u> | County<br><u>Chaves</u> |
| Drilling<br>Contractor<br><u>Fred Pool</u>                            |                                                    | Type of Equipment<br><u>Rotary</u> |                       |                    |                         |
| 1 * witness<br>2 * witness if possible <u>APPROVED CASING PROGRAM</u> |                                                    |                                    |                       |                    |                         |

| Size of Hole       | Size of Casing | Weight Per<br>60' Foot | New or Used | Depth        | Sacks Cement         |
|--------------------|----------------|------------------------|-------------|--------------|----------------------|
| <u>24"</u>         | <u>20"</u>     |                        |             | <u>40'</u>   | <u>Red. mix</u>      |
| 1 * <u>17 1/2"</u> | <u>13 3/8"</u> | <u>54#</u>             |             | <u>700'</u>  | <u>450 SX - Circ</u> |
| 2 * <u>12 1/4"</u> | <u>8 5/8"</u>  | <u>24#</u>             |             | <u>1200'</u> | <u>650 SX - Circ</u> |
| <u>7 7/8"</u>      | <u>4 1/2"</u>  | <u>10.5#</u>           |             | <u>6000'</u> | <u>800 SX</u>        |

Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch \_\_\_\_\_ # Grade \_\_\_\_\_  
(Approved) (Rejected) \_\_\_\_\_

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required 200

Type of Shoe used Guide Float collar used Insert Btm 3 jts welded Yes

TD of hole 1250 Set 1257 Feet of 8 5/8 Inch 24 # Grade J-55

New-used csg. @ 1257 with 200 sacks neat cement around shoe  
+ 225 sax Haw-Co Lite additives

Plug down @ 5.00 (AM) (PM) Date 12-30-80

Cement circulated Yes No. of Sacks 160 SX

Cemented by Hawco Witnessed by B.W.W

Temp. Survey ran @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_ top cement @ \_\_\_\_\_

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: 3 Centrifugers