

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Mesa Petroleum Corp</u>		Lease <u>Round Top State</u>		Well # <u>4</u>	
Location of Well	Unit <u>1980N 1980W F</u>	Section <u>9</u>	Township <u>7</u>	Range <u>23</u>	County <u>Chaves</u>
Drilling Contractor	<u>Desert</u>		Type of Equipment <u>Rotary</u>		
*Witness					
APPROVED CASING PROGRAM					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>12 1/4</u>	<u>8 5/8</u>	<u>24 #</u>		<u>1400</u>	<u>Circ</u>
<u>7 7/8</u>	<u>4 1/2</u>	<u>10.5 #</u>		<u>3500</u>	
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected)					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>12 1/4</u> Size of Casing <u>8 5/8</u> Sacks cement required _____					
Type of Shoe used <u>Guide</u> Float collar used <u>Float</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>1625</u> Set <u>1623</u> Feet of <u>8 5/8</u> Inch <u>24</u> # Grade <u>J-55</u>					
New-used csg. @ <u>8 5/8</u> with <u>200</u> sacks neat cement around shoe					
+ <u>800 Hanco</u> ^{Life} <u>Sax</u> <u>300 Thick Set</u> additives					
Plug down @ <u>630</u> (AM) (PM) Date <u>8-13-81</u>					
Cement circulated <u>NO</u> No. of Sacks _____					
Cemented by <u>Hanco</u> Witnessed by <u>Blw Weaver</u>					
Temp. Survey ran @ <u>300</u> (AM) (PM) Date <u>8-13-81</u> top cement @ <u>600</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>Ran Temperature Survey 8-13-81 Top Cement @ 600</u>					

1st stage Top Cement @ 558 Ran 200 SX Thickset
2nd stage Tag @ 496 Ran 200 SX Thick Set
3rd stage Tag @ 674 Ran 200 SX "
4th stage Tag @ 671 Ran 200 SX "
5th ~~Tag~~ Tag @ 510 Ran 200 SX "
6th stage Tag @ 493 Ran 200 SX "
7th stage Tag @ 320 Ran 50 SX "
8th Ran 1" Tagged to 2172' Pumped 200sx Thick set
9. Ran 1" Tagged to 245' Pumped 32sx Thickset.