

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Amended for.

Operator <u>Mesa Petr Co.</u>		Lease <u>NED State</u>		Well # <u>3</u>	
Location of Well	Unit <u>L</u>	Section <u>8</u>	Township <u>9</u>	Range <u>23</u>	County <u>Chaves</u>
Drilling Contractor	<u>1980-S</u> <u>660-W</u> <u>Desert Drilling</u>		Type of Equipment <u>Rotary</u>		
<u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
* <u>12 1/4"</u>	<u>8 5/8"</u>	<u>34 #</u>		<u>1400'</u>	<u>750</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>10.5 #</u>		<u>3700'</u>	<u>500</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>12 1/4"</u> Size of Casing <u>8 5/8"</u> Sacks cement required _____					
Type of Shoe used <u>guide</u> Float collar used <u>insert</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>1145'</u> Set <u>1145'</u> Feet of <u>8 5/8"</u> Inch <u>24</u> # Grade <u>K-55</u>					
New-used csg. @ <u>1145'</u> with <u>200 29cc</u> sacks neat cement around shoe					
+ <u>200</u> sax <u>Hol. etc</u> additives (<u>1/4# floreal, 49cc</u>)					
Plug down @ <u>12:00</u> (AM) (PM) Date <u>10/1/81</u>					
Cement circulated <u>No</u> No. of Sacks <u>0</u>					
Cemented by <u>Halliburton</u> Witnessed by <u>Mike Stillfield</u>					
Temp. Survey ran @ <u>7:30</u> (AM) (PM) Date <u>10/1/81</u> top cement @ <u>585'</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: + <u>125 sx Thixret (49cc)</u>					
+ <u>200 sx H/L (1# floreal, 29cc)</u>					
+ <u>125 sx Thixret (49cc)</u>					
+ <u>200 sx H/L (1# floreal, 29cc)</u> with @ 90'-585'					
+ <u>125 sx Thixret (49cc)</u>					

1. Ran 1" + Tagged to c @ 640'
Pumped 5 BBL floreal + 200sx Thixret
2. Ran 1" + Tagged to c @ 527'
Pumped 5 BBL floreal + 200sx Thixret
3. Ran 1" + Tagged to c @ 192'
Pumped 5 BBL floreal + 200sx Thixret

4. Ran 1" + Tagged to c @ 90'
Pumped
cement circulated to surface.