

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>YPC</u>		Lease <u>SNAKEWEED SD</u>		Well # <u>1</u>	
Location of Well	Unit <u>N</u>	Section <u>36</u>	Township <u>7S</u>	Range <u>24</u>	County <u>CHAVES</u>
Drilling Contractor	<u>L/M</u>		Type of Equipment <u>ROTARY</u>		

APPROVED CASING PROGRAM

*** WITNESS**

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cemen
<u>17 1/2</u>	<u>13 3/8</u>	<u>54</u>	<u>NEW</u>	<u>441</u>	<u>CIRC</u>
<u>* 12 1/4</u>	<u>8 5/8</u>	<u>24#</u>	<u>NEW</u>	<u>1000</u>	<u>CIRC</u>
<u>6 1/4</u>	<u>TD</u>	<u>9.5</u>	<u>"</u>	<u>4050</u>	<u>350 SX</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required 1000

Type of Shoe used WIDE Float collar used INSE Btm 3 jts welded YES

TD of hole 1000 Set 1000 Feet of 8 5/8 Inch 24 # Grade J-55

(New) used csg. @ 1000 with 300 sacks neat cement around shoe cl.c 3% CaCl₂
+ 700 sax HALU LITE additives 1/4# floccle, 5# Gilsomite, 2% CaCl₂

Plug down @ 2:30 (AM) (PM) Date 3-16-84

Cement circulated _____ No. of Sacks _____

Cemented by _____ Witnessed by _____

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____