

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Corp</u>		Lease <u>Rook "RK" St.</u>		Well # <u>4</u>	
Location of Well	Unit <u>1980 N</u> <u>6600 W</u> <u>E</u>	Section <u>2</u>	Township <u>8</u>	Range <u>25</u>	County <u>Chaves</u>
Drilling Contractor	<u>Kennel #</u> <u>HORTON</u>		Type of Equipment <u>ROTARY</u> <u>ASAP</u>		

* WITNESS

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>12 1/4</u>	<u>10 3/4"</u>	<u>40.5# J-55</u>		<u>900'</u>	<u>550 SX. Circ</u>
<u>7 7/8</u>	<u>4 1/2</u>	<u>9.5#</u>		<u>4250'</u>	<u>350 SX.</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 14 3/4 Size of Casing 10 3/4 Sacks cement required 800

Type of Shoe used GUIDE Float collar used INSERT Btm 3 jts welded YES

TD of hole 925 Set 925 Feet of 10 3/4 Inch 40.5 # Grade J-55

(New) used csg. @ 925 with 300 sacks neat cement around shoe C.I.C w/2% CaCl₂
+ 500 sax PACESETTER "C" additives 3% CaCl

Plug down @ 4:00 (AM) (PM) PM Date 3/21/82

Cement circulated Yes No. of Sacks 50 to the pit

Cemented by Western Witnessed by Larry Brooks

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____