

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

EST  
Sun

|                             |                                |                       |                          |          |               |
|-----------------------------|--------------------------------|-----------------------|--------------------------|----------|---------------|
| Operator Mesa Petroleum Co. |                                | Lease Round Top State |                          | Well # 7 |               |
| Location of Well            | Unit G                         | Section 10            | Township 7               | Range 23 | County Chaves |
| Drilling Contractor         | 1780/N<br>1980/E<br>Dual Drly. |                       | Type of Equipment Rotary |          |               |

\* witness

APPROVED CASING PROGRAM

| Size of Hole | Size of Casing | Weight Per Foot | New or Used | Depth | Sacks Cement |
|--------------|----------------|-----------------|-------------|-------|--------------|
| * 12 1/4"    | 8 5/8"         | 24#             |             | 1400' | 300/300/300  |
| 7 7/8"       | 4 1/2"         | 10.5#           |             | 3400' | 500/500      |
|              |                |                 |             |       |              |

Casing Data:

Surface joints of 8 5/8" inch 24 # Grade J-55  
(Approved) (Rejected)

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole 12 1/4" Size of Casing 8 5/8" Sacks cement required

Type of Shoe used guide Float collar used Insert Btm 3 jts welded yes

TD of hole 1482' Set 1476' Feet of 8 5/8" Inch 24 # Grade K-55

New+used csg. @ 1476' with 200 sacks neat cement around shoe  
+ 700 sax H/L thixret additives 1/4# colored, 4% cc

Plug down @ 3830 (AM) (PM) Date 5/16/82

Cement circulated No No. of Sacks -0-

Cemented by Halliburton Witnessed by M.E.

Temp. Survey ran @ 930 (AM) (PM) Date 5/16/82 top cement @ 760'

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks:

lost circ @ 360'

centralizers @ 1436'-1356'-1276' lost dily break @ 1155'

1. Run 1" + Tagged toc @ 775'

Pumped 300 sx C 4% cc

2. Run 1" + Tagged toc @ 685'

Pumped 200 sx C 4% cc

3. Run 1" + Tagged toc @ 450'

Pumped 100 sx C 4% cc

4. Run 1" + Tagged toc @ 83'

Pumped 34 sx C 4% cc

Cement circulated to surface.