

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Mesa Petr. Co.</u>		Lease <u>Haley Corn</u>		Well # <u>1</u>	
Location of Well	Unit <u>F</u>	Section <u>7</u>	Township <u>7</u>	Range <u>23</u>	County <u>Chaves</u>
Drilling Contractor	<u>Dual Drly. Co.</u>		Type of Equipment <u>Rotary</u>		

* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>12 1/4</u>	<u>8 5/8</u>	<u>24 #</u>		<u>1400</u>	<u>700/300</u> ^{circ.}
<u>7 7/8</u>	<u>4 1/2</u>	<u>10.5 #</u>		<u>3100</u>	<u>300</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required _____

Type of Shoe used _____ Float collar used _____ Btm 3 jts welded _____

TD of hole _____ Set _____ Feet of _____ Inch _____ # Grade _____

New-used csg. @ _____ with 200 sacks neat cement around shoe cl. c w/ 2% CaCl₂
+ 700 sax Thicset Lite additives 1/4# floccle, 4% CaCl₂,

Plug down @ _____ (AM) (PM) Date _____

Cement circulated _____ No. of Sacks _____

Cemented by _____ Witnessed by For record only.

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ 310'

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: Tagged @ 305' pumped 200 sxs. cl. c w/ 4% CaCl₂

Tagged @ ~~310~~ 270' " " " " " " "

Tagged @ ~~270~~ 180' " 225 sxs. cl. c w/ 4% CaCl₂ & circ. ²⁵ sxs.

In the pit