

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator Yates Pet. Co.		Lease Chaves UY St.		Well # 1	
Location of Well	Unit A	Section 32	Township 8 S	Range 25 E	County Chaves
Drilling Contractor	La Rue/Muncy		Type of Equipment Rotary		

* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
* 17 1/2"	13 3/8	48#	New	800	CIRC
7 7/8"	4 1/2	9.5#	"	TD	350 Sxs.

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 17 1/2" Size of Casing 13 3/8" Sacks cement required 750 initial 200 sxs 1"

Type of Shoe used Guide ^{Te. Pat.} Float collar used insert Btm 3 jts welded yes

TD of hole 800' Set 800' Feet of 13 3/8" Inch 48 # Grade J-55

New-used csg. @ 800' with 250 sacks neat cement around shoe C.I.C 2% CaCl₂ + 50 sax thickset (Lite) additives + 450 sxs. H. Lite, 1/4# flocele, 4% CaCl₂

Plug down @ 10:30 (AM) (PM) Date 11/6/82

Cement circulated NO No. of Sacks _____

Cemented by HALLIBURTON Witnessed by Larry Brooks

Temp. Survey ran @ 4:30 (AM) (PM) Date 11/6/82 top cement @ 145'

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: Tagged w/ 1" in soft non-cured cement @ 125'

Pumped 200 sxs C.I.C 2% CaCl₂, circ. 15 sxs. to the pit.