

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Co.</u>		Lease <u>Bajillo Draw WQ St.</u>		Well # <u>3</u>	
Location of Well	Unit <u>B</u>	Section <u>28</u>	Township <u>7S</u>	Range <u>23E</u>	County <u>Chaves</u>
Drilling Contractor	<u>NA</u>		Type of Equipment <u>Rotary</u>		

*** Witness** APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
* <u>14 3/4</u>	<u>10 3/4</u>	<u>40.5</u>	<u>New</u>	<u>1100</u>	<u>CIRC</u>
<u>7 7/8</u>	<u>4 1/2</u>	<u>9.5</u>	<u>"</u>	<u>TD</u>	<u>350 Sx.</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 14 3/4 Size of Casing 10 3/4 Sacks cement required _____

Type of Shoe used TEX. PT. Float collar used insert Btm 3 jts welded yes

TD of hole 1100 Set 1100 Feet of 10 3/4 Inch 40.5 # Grade J-55

New-used csg. @ 1100' with 300 sacks neat cement around shoe C.I.C. 2% CaCl₂
+ 400 sax PACESSETTER LITE additives 1/4 # celoplake + 5# Hicele + 3% CaCl₂

Plug down @ 5:00 (AM) (PM) Date 7/23/83

Cement circulated NO No. of Sacks _____

Cemented by WESTERN Witnessed by Larry Brook

Temp. Survey ran @ 11:00 (AM) (PM) Date 7/23/83 top cement @ 500'

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: TAGGED AT 500' PUMPED 50 SXS. C.I.C 4% CaCl₂ WOC TAGGED AT
425', PUMPED 50 SXS. C.I.C 4% CaCl₂ CMT. 50' FM. BIT M ON
1" NO FLUID LEVEL (H₂O) REDIMMED W/ 8 YDS.
LC 145 @ 465'