

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 10
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Carter Drilling Co.</u>		Lease <u>San Juan #1</u>		Well # <u>7</u>	
Location of Well	Unit <u>5-55</u>	Section <u>23</u>	Township <u>1N</u>	Range <u>2S</u>	County <u>Sandoz</u>
Drilling Contractor	<u>Carter Drilling Co.</u>		Type of Equipment <u>Ritter</u>		

APPROVED CASING PROGRAM 4-12-71

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>9 1/8"</u>	<u>7"</u>	<u>26</u>		<u>1150</u>	<u>line</u>
<u>1 1/2"</u>	<u>10-5 1/2"</u>	<u>9.55 15.5"</u>		<u>1500</u>	<u>line</u>

Casing Data: 10"-128-100

Surface 30 joints of 7" inch 23 # Grade API 5-55 + N80
LT+C used (Approved) (~~Rejected~~)

Inspected by Bessett date 4-14-71

Cementing Program 1378-225
9 1/8" 890

Size of hole 9 1/8" Size of Casing 7" Sacks cement required

Type of Shoe used Guide Float collar used off Btm 3 jts welded head Lock

TD of hole 1160 ^{DF} Set Feet of 7" Inch 23 # Grade 5-55 + N80

~~Non~~-used csg. @ 1150 ^{DF} with 150 sacks neat cement around shoe
+ 300 sacks Super 7091 + 27000 additives + fluoride + Silsonite (6%)

Plug down @ 12:10 (~~AM~~) (PM) Date 4-16-71

Cement circulated no No. of Sacks

Cemented by Denton Witnessed by Bessett

Temp. Survey ran @ 7:30 (~~AM~~) (PM) Date 4-16-71 top cement @ 660

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: 200 90' at 10-128-100 - 200 810 Centalizing @ 722 + 1022 Depth 681 + 808

1" to 445 Cemented w/ 75 sacks neat + 4% CC in @ 10:30 PM recirc.

1" to 317 " " " " @ 7:00 AM 4-17-71 recirc. FL 140

1" to 294 " " " " @ 6:35 AM " "

1" to 210 " " " " @ 9:35 AM " "

1 1/2" to surface w/ 3 1/2 sacks Neale's mix @ 10:45 AM 4-17-71