

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Gates Pet. Corp.</i>		Lease <i>J. Lacy J.</i>		Well # <i>13</i>	
Location of Well	Unit <i>1980N+E</i>	Section <i>22</i>	Township <i>17</i>	Range <i>25</i>	County <i>Eddy</i>
Drilling Contractor <i>Byrd & Co.</i>		Type of Equipment <i>Rotary</i>			

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>15</i>	<i>10 3/4</i>	<i>32</i>		<i>300</i>	<i>Circ.</i>
<i>9 1/2</i>	<i>7</i>	<i>20</i>		<i>1150</i>	<i>"</i>
<i>6 1/4</i>	<i>4 1/2 + 5 1/2</i>	<i>10.5 + 15.5</i>		<i>1500</i>	<i>"</i>

Casing Data:

Surface *32* joints of *7* inch *23* # Grade *J-55* used.
(Approved) (Rejected)

Inspected by _____ date _____

Cementing Program

Size of hole *9 1/2* Size of Casing _____ Sacks cement required _____

Type of Shoe used *Link* Float collar used _____ Btm 3 jts welded *thru hole*

TD of hole *1160* Set *1160* Feet of *7* Inch *23* # Grade *J-55*

New-used csg. @ *1160* with *150* sacks neat cement around shoe @ *2900*
+ *350* sack *mix* - *4 lb* additives + *4 lb* + *2500*

Plug down @ *9:00* (AM) (PM) Date *8-11-76*

Cement circulated *yes* No. of Sacks *505*

Cemented by *Denton* Witnessed by _____

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: *10 3/4 - 345-225 SX C - 4200 PD 7:30 AM, 8-9-76 circ. 4054, Pressure 1054*

centralizer - 1195 + 1117 Baskets @ 463 + 528 - They 1000 1000

mixed pit - mixed w/ lost circ. material - got return - cement fell

3:30 PM. Leon called - cement fell back 60' filled w/ Redmud, @ 3:00 PM, 8-11-76