

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 110
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet Corp</u>		Lease <u>Morris Estate CC</u>		Well # <u>7</u>	
Location of Well	Unit <u>3305 P 9905</u>	Section <u>15</u>	Township <u>17</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>L. Rue #2</u>		Type of Equipment <u>Rotary</u>		
*witness					
<u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>1 1/2</u>	<u>10 3/4"</u>	<u>30#</u>		<u>350'</u>	<u>Circ</u>
* <u>9 1/2</u>	<u>7"</u>	<u>23#</u>		<u>1150'</u>	<u>Circ</u>
<u>6 1/4</u>	<u>4 1/2"</u>	<u>95#</u>		<u>1500'</u>	<u>125 SX</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected)					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>9 7/8"</u> Size of Casing <u>7"</u> Sacks cement required _____					
Type of Shoe used <u>guide</u> Float collar used <u>ment</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>1160'</u> Set <u>1160'</u> Feet of <u>7"</u> Inch <u>23</u> # Grade <u>3-55</u>					
<u>New</u> -used csg. @ <u>1160'</u> with <u>175 28</u> sacks neat cement around shoe					
+ <u>250</u> sax <u>Paceretter C</u> additives (<u>10# gelonite, 1/4# caloxol, 390cc</u>)					
Plug down @ <u>10:45</u> (AM) (PM) Date <u>3/24/83</u>					
Cement circulated <u>No</u> No. of Sacks <u>-0-</u>					
Cemented by <u>Western Co</u> Witnessed by <u>Miles Stubbfield</u>					
Temp. Survey ran @ <u>5:00</u> (AM) (PM) Date <u>3/25/83</u> top cement @ <u>210'</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks:					
<u>lost circ @ 215'</u>					
<u>lost dily break @ 1050'</u>					

- No centralizers or risers
1. Ran 1" + tagged TOC @ 500'
Pumped 100 sx @ 490cc
 2. Ran 1" + tagged TOC @ 480'
Pumped 25 sx @ 490cc
 3. Ran 1" + Tagged TOC @ 385'
Pumped 110 sx @ 490cc
cement circ. O.T.T.