

NEW MEXICO OIL CONSERVATION COMMISSION
 DRAWER 10
 ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>David Fester</u>		Lease <u>State 32 Com</u>		Well # <u>1</u>	
Location of Well	Unit <u>1000NW</u>	Section <u>32</u>	Township <u>20</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>Walter & Co.</u>		Type of Equipment <u>Rotary to Start 12-5-73</u>		
<u>APPROVED CASING PROGRAM 11-30-73</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>48</u>		<u>200</u>	<u>200 Cms</u>
<u>12 1/4"</u>	20 <u>8 5/8"</u>	<u>24+32</u>		<u>3200</u>	<u>900 Cms.</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>11.6</u>		<u>9800</u>	<u>450</u>
Casing Data:					
Surface <u>87</u> joints of <u>8 3/4</u> inch <u>32+24</u> # Grade <u>API New K-55</u> (Approved) (Rejected)					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>12 1/4</u> Size of Casing <u>8 5/8</u> Sacks cement required <u>1025</u>					
Type of Shoe used <u>Wide</u> Float collar used <u>Insert</u> Btm 3 jts welded _____					
TD of hole <u>3245.22</u> Set <u>3242</u> Feet of <u>8 5/8</u> Inch <u>32+24</u> # Grade <u>K-55</u>					
New-used csg. @ <u>3242</u> with <u>25</u> sacks neat cement around shoe Class C 2% cc 14.8 + <u>1000</u> sax <u>Novaco Lite</u> additives <u>1/2" Flo rate 2% cc 12.8</u>					
Plug down @ <u>5:00</u> (AM) (PM) Date <u>1-2-74</u>					
Cement circulated <u>Yes</u> No. of Sacks <u>566 1/2</u> good cement					
Cemented by <u>Halliburton</u> Witnessed by <u>None</u>					
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>Had 200/51 Class C on loc. but could not transfer from bulk truck, Tried for 45 mins. then pumped plug down. WOC 30 hrs.</u>					

Nit witness