

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

31P

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Co.</u>		Lease <u>Stonewall EP ST.</u>			Well # <u>7</u>
Location of Well	Unit <u>D</u>	Section <u>30</u>	Township <u>20S</u>	Range <u>20E</u>	County <u>EDDY</u>
Drilling Contractor	<u>L/M 2</u>		Type of Equipment <u>ROTARY</u>		

* Witness APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>13 3/8</u>	<u>48</u>	<u>NEW</u>	<u>550</u>	<u>CIRC</u>
* <u>12 1/4</u>	<u>8 5/8</u>	<u>24-28</u>	<u>"</u>	<u>2400</u>	<u>CIRC</u>
<u>7 7/8</u>	<u>5 1/2</u>	<u>17-20</u>	<u>"</u>	<u>TD</u>	<u>TIE BK.</u>

Casing Data:

Surface joints of inch # Grade
(Approved) (Rejected)

Inspected by date

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required

Type of Shoe used Tex-Pat Float collar used INSERT Btm 3 jts welded YES

TD of hole 2371 Set 2372 Feet of 8 5/8 Inch 24 # Grade J-55

New-used csg. @ 2372 with 450 sacks neat cement around shoe
+ 500 sax Class C 4% Gel additives #3 Gilsonite 2% CC

Plug down @ 2:30 (AM) (~~PM~~) Date 12-15-83

Cement circulated NO No. of Sacks

Cemented by Western Witnessed by B. U. Weaver

Temp. Survey ran @ 8:30 (AM) (~~PM~~) Date 12-15-83 top cement @ 360

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Loss Zone @ 1023 Lat Drilling Break @ 2180

Ran 1" Tag @ 315 Ran 150 SX @ 2% CC cure cement