
一种型。是10色	DEPARTMENT OF THE INTERI		FORMAPPROVED OM B No. 1004-0137 Expires: March 31, 2007
/	BUREAU OF LAND MANAGEMEN		5. Lease Serial No.
CEPT 75HYDBY	NOTICES AND REPORTS	ON WELLS	LC-057210
SEP To 7 no Class ti	his form for proposals to drill o	r to re-enter an	6. If Indian, Allottee or Tribe Name
LI Capandoneo W	ell. Use Form 3160-3 (APD) for	such proposals.	!
SUBMIT IN TR	IPLICATE - Other instructions	on reverse side.	7. If Unit or CA/Agreement, Name and/or No
1. Type of Well X Oil Well	Gas Well X Other		
			8. Well Name and No.
2 Name of Operator ConocoPhillips Company	v (#217817)		9. API Well No.
3a. Address	· · · · · · · · · · · · · · · · · · ·	No.(include area code)	30-025- San AHache
3300 N. "A" Street, Bldg.		2)688-6884	10. Field and Pool, or Exploratory Area
4. Location of Well (Footage, Se	ec., T., R., M., or Survey Description)		Maljamar; Grayburg-San Andres
T-17-S, R-32-E & R-33-E	-		11. County or Parish, State
			Lea
12 CUECK AI		E NATURE OF NOTICE D	New Mexico
	PPROPRIATE BOX(ES)TO INDICAT		EPORT, OR OTHER DATA
TYPE OF SUBMISSION		TYPEOF ACTION	
X Notice of Intent	Acidize Deepen	Production (Sta	
	AlterCasing Fracture	_	Well Integrity
Subsequent Report	[TT7]	nstruction Recomplete	Other
Final Abandonment Notice	Convert to Injection Plug Bac	Abandon Temporarily Ab	andon
		1	any proposed work and approximate duration thereof
following completion of the inv	volved operations. If the operation results in a m nal Abandonment Notices shall be filed only afte	ultiple completion or recompletion i	red subsequent reports shall be filed within 30 days in a new interval, a Form 3160-4 shall be filed once nation, have been completed, and the operator has
Ref. Bond #ES0085			
Referencing Master Drilli submit the attached mod	ing Plan on file with the BLM Car lifications to the cement program	dsbad office dated 02/28 sections of the Master l	/2008. ConocoPhillips wishes to Drilling Plan:
Pg. 7 8-5/8" Surf. Csg	. Lead Slurry Density Change fro	m 13 1 to 13 5 ppg	The same of the sa
Pg. 7 WOC time chan	ge from 24 to 18 hrs.		APPROVED
Pg. 8 5-1/2" Prod. Csg	g. Tail Slurry Density Change from	n 16.4 to 14.8 ppg	
Pg. 9 5-1/2" Prod. Csg Pg. 11 5-1/2" Prod. Csg	j. Tail Slurry Density Change fromj. Tail Slurry Density Change from	n 16.4 to 14.8 ppg	0.50
			SEP 2 2008
Opdated pages are attac	hed for your convience to insert	into the master documer	LES BABYAK
	this request is greatly appreciate	ed.	PETROLEUM ENGINEER
 I hereby certify that the foregone Name (Printed/Typed) 	oing is true and correct	1	The state of the s
Celeste G. Dale		Title Regulatory Spec	ialist
Signature (allet	e Anlale	Date 06/16/2008	
	THIS SPACE FOR FEDERAL	OR STATE OFFICE L	JSE
Approved by	tracked Assessed of the	Title	Date
	ttached. Approval of this notice does not warr or equitable title to those rights in the subject		-
which would entitle the applicant to		lease Office	7

Tide 18 U.S.C. Section 1001 and Title 43 U.S.C. Section 1212, make it a crime for any person knowingly and willfully to make to any department or agency of the United States any false, fictitious or fraudulent statements or representations as to any matter within its jurisdiction.

(Instructions on page 2)



4. Proposed cementing program:

For the cementing program a range is presented for the number of sacks of cement and for the bottom, top, and length of the lead slurries and tail slurries due to the variation in formation tops and planned TD for the planned / contemplated wells for which this Master Drilling Plan is intended.

13-3/8" Conductor:

Cement to surface with ready mix or Class C Neat cement. TOC at surface.

8-5/8" Surface Casing:

The intention for the cementing program for the Surface Casing is to:

- Place the Tail Slurry from the casing shoe to 300' above the casing shoe,
- Bring the Lead Slurry to surface.

Spacer: 20 bbls Fresh Water

Volume (sx) & Recipe & Excess %	Bottom (ft MD)	Top (ft MD)	Length (ft)	Density (ppg)	Yield (cuft/sx)	Mix Wtr gal/sx	Compressive Stre @ 85 deg F by UCA	
185 – 535 sx Class C + 6% bentonite + 2% CaCl2 + 0.125% Polyflake	325 to 940	Surface	325 to 940	13.5	1.96	10.69	Time 12 hrs 18 hrs 24 hrs	Strength 316 psi 417 psi 506 psi
Excess = 170%								

Tail Slurry								
Volume (sx) & Recipe & Excess %	Bottom (ft MD)	Top (ft MD)	Length (ft)	Density (ppg)	Yield (cuft/sx)	Mix Wtr gal/sx	Compressive Strength @ 91 deg F by UCA Met	
220 sx Class C + 2% CaCl2 + 0.125% Polyflake Excess = 100%	625' to 1240'	325' to 940'	300'	14.8	1.35	6.36	Time 3 hrs 9 hrs 12 hrs 24 hrs 48 hrs	Strength 50 psi 500 psi 793 psi 1266 psi 2183 psi

Displacement: Fresh Water

Note: In accordance with the Pecos District Conditions of Approval, we will Wait on Cement (WOC) for a period of not less than 18 hrs after placement of the cement on the Surface Casing in order to achieve at least 500 psi compressive strength in both the Lead Slurry and Tail Slurry cements prior to drilling out of the Surface Casing.

5-1/2" Production Casing Cementing Program - Single Stage Cementing Option:

The intention for the cementing program for the Production Casing – Single Stage Cementing Option is to:

- Place the Tail Slurry from the casing shoe to the top of the Grayburg formation,
- Bring the Lead Slurry to surface.

Spacer: 20 bbls Fresh Water with an option to follow this with 1000 gallons SuperFlush 102 and 20 additional bbls Fresh Water.

Volume (sx) & Recipe & Excess %	Bottom (ft MD)	Top (ft MD)	Length (ft)	Density (ppg)	Yield (cuft/sx)	Mix Wtr gal/sx	. Stre @ 113	oressive engths deg F by Method
433 – 644 sx 50% Class C 50% POZ + 10% bentonite + 8 lb/sx Salt + 0.2% Fluid Loss Additive + 0.125% Polyflake	3270' to 3940'	Surface	3270' to 3940'	11.8	2.55	14.88	Time 12 hrs 24 hrs 48 hrs 72 hrs	Strength 100 psi 200 psi 245 psi 310 psi

Volume (sx)	Bottom	Top	Length	Density	Yield	Mix Wtr	Compressive Strengths	
& Recipe & Excess %	(ft MD)	(ft MD)	(ft)	(ppg)	(cuft/sx)	gal/sx	@ 115 deg F by UCA Meth	
150 – 285 sx 65% Class C 35% POZ + 0.4% Dispersant	4155' to 4705'	3270' to 3940'	636' to 885'	14.8	0.98	3.76	Time 5 hrs 56 min 8 hrs 12 min 24 hrs 48 hrs 72 hrs	Strength 50 psi 500 psi 2806 psi 4690 psi 5661 psi

Displacement: 2% KCL water with approximately 250 ppm gluteraldehyde biocide.

5-1/2" Production Casing Cementing Program - Two-Stage Cementing Option (for Loss of Circulation Events):

We propose an option to use the two-stage cementing method for cementing the production casing if any loss of circulation events or heavy seepage is experienced while drilling the 7-7/8" hole. (see discussion in Item 3 above). The proposed two-stage cementing program would be as follows:

- Stage 1: Would place cement from the casing shoe to the stage tool.
- Stage 2: Would place cement from the stage tool to Surface.

Stage 1:

Spacer: 20 bbls Fresh Water with an option to follow this with 1000 gallons SuperFlush 102 and 20 additional bbls Fresh Water

Stage 1 - Lead Surry: None

Volume (sx)	Bottom	Top	Length	Density	Yield	Mix Wtr	Compressive Strengths @ 113 deg F by Crush Meth	
& Recipe & Excess %	(ft MD)	(ft MD)	(ft)	(ppg)	(cuft/sx)	gal/sx		
150 – 285 sx 65% Class C 35% POZ + 0.4% Dispersant	4155' to 4705'	3270' to 3940'	636' to 885'	14.8	0.98	3.76	Time 5 hrs 56 min 8 hrs 12 min 24 hrs 48 hrs 72 hrs	Strength 50 psi 500 psi 2806 psi 4690 psi 5661 psi

Displacement: A volume of Fresh Water equal to the capacity volume from the stage tool to the float collar, followed by brine based mud.

5-1/2" Production Casing Cementing Program – Two-Stage Cementing Option with Stage Tool and External Casing Packers (for Water Flow Events):

We propose an option to use the two-stage cementing method with a Stage Tool and two each External Casing Packers if any waterflow event is experienced while drilling the 7-7/8" hole as discussed above in Item 3. The proposed two-stage cementing program would be as follows:

- Stage 1: Would place cement from the casing shoe to the stage tool
- Stage 2: Would place cement from the stage tool to Surface.

Stage 1:

Spacer: 20 bbls Fresh Water with an option to follow this with 1000 gallons SuperFlush 102 and 20 additional bbls Fresh Water

Stage 1 – Lead Slurry Volume (sx)	Bottom	Top	Length	Density	Yield (cuft/sx)	Mix Wtr gal/sx	Compressive @ 113 deg F by 0	
& Recipe & Excess % 77 – 363 sx 50% Class C 50% POZ + 10% bentonite + 8 lb/sx Salt + 0.2% Fluid Loss Additive + 0.125% Polyflake	(ft MD) 3270' to 3940'	(ft MD) 1670' to 3440'	500' to 1600'	(ppg) 11.8	2.55	14.88	Time 12 hrs 24 hrs 48 hrs 72 hrs	Strength 100 psi 200 psi 245 psi 310 psi

Volume (sx)	Bottom	Top	Length	Density	Yield	Mix Wtr	Compressive Strengths @ 113 deg F by Crush Meth	
& Recipe & Excess %	(ft MD)	(ft MD)	(ft)	(ppg)	(cuft/sx)	gal/sx		
150 – 285 sx 65% Class C 35% POZ + 0.4% Dispersant	4155' to 4705'	3270' to 3940'	636' to 885'	14.8	0.98	3.76	Time 5 hrs 56 min 8 hrs 12 min 24 hrs 48 hrs 72 hrs	Strength 50 psi 500 psi 2806 psi 4690 psi 5661 psi

Displacement: A volume of Fresh Water equal to the capacity volume from the stage tool to the float collar, followed by brine based mud.