

NO. OF COPIES RECEIVED		
DISTRIBUTION		
SANTA FE		
FILE		
U.S.G.S.		
LAND OFFICE		
OPERATOR		

NEW MEXICO OIL CONSERVATION COMMISSION

Form C-103
Supersedes Old
C-102 and C-103
Effective 1-1-65

5a. Indicate Type of Lease	
State <input type="checkbox"/>	Fee <input checked="" type="checkbox"/>
5. State Oil & Gas Lease No.	

SUNDRY NOTICES AND REPORTS ON WELLS (DO NOT USE THIS FORM FOR PROPOSALS TO DRILL OR TO DEEPEN OR PLUG BACK TO A DIFFERENT RESERVOIR. USE "APPLICATION FOR PERMIT" (FORM C-101) FOR SUCH PROPOSALS.)

1. OIL WELL <input checked="" type="checkbox"/> GAS WELL <input type="checkbox"/> OTHER- <input type="checkbox"/>	7. Unit Agreement Name
2. Name of Operator Oil Development Company of Texas	8. Farm or Lease Name SFPRR
3. Address of Operator 900 Polk Street, Amarillo, Texas 79101	9. Well No. 9
4. Location of Well UNIT LETTER F , 1980 FEET FROM THE North LINE AND 2180 FEET FROM THE West LINE, SECTION 28 TOWNSHIP 9S RANGE 37E NMPM.	10. Field and Pool, or Wildcat West Sawyer (San Andres)
15. Elevation (Show whether DF, RT, GR, etc.) 3972 GL, 3983' RKB	12. County Lee

Check Appropriate Box To Indicate Nature of Notice, Report or Other Data NOTICE OF INTENTION TO: SUBSEQUENT REPORT OF:

PERFORM REMEDIAL WORK <input type="checkbox"/>	PLUG AND ABANDON <input type="checkbox"/>	REMEDIAL WORK <input type="checkbox"/>	ALTERING CASING <input type="checkbox"/>
TEMPORARILY ABANDON <input type="checkbox"/>	CHANGE PLANS <input type="checkbox"/>	COMMENCE DRILLING OPNS. <input type="checkbox"/>	PLUG AND ABANDONMENT <input type="checkbox"/>
PULL OR ALTER CASING <input type="checkbox"/>	OTHER <input type="checkbox"/>	CASING TEST AND CEMENT JOBS <input checked="" type="checkbox"/>	OTHER <input type="checkbox"/>

17. Describe Proposed or Completed Operations (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work) SEE RULE 1103.

Spud date 11-8-70. Ran 10 jts 8-5/8" 20# casing, set at 416' RKB.
Cemented w/325 sx Class A w/2% CaCl₂. Plug down at 8:15 p.m. 11-9-70.
Cement circulated. Tested to 750 psi. WOC 12 hours.

Casing was cemented in accordance with Option 2 as follows:

1. Volume of slurry - 354 cu. ft., Southwestern Type H, API Class A w/2% CaCl₂.
2. Approximate temperature of slurry - 78° F.
3. Estimated minimum formation temperature - 92° F.
4. Estimated cement strength at time of testing - 1310 psi.
5. Actual time cement in place prior to starting test - 12 hrs.

18. I hereby certify that the information above is true and complete to the best of my knowledge and belief.

SIGNED Larry D. Farrell TITLE Petroleum Engineer DATE November 16, 1970
APPROVED BY John W. Runyan TITLE Inspector DATE NOV 18 1970
CONDITIONS OF APPROVAL, IF ANY:

RECEIVED

NOV 17 1970

OIL CONSERVATION COMM.
10320. 1. 1.