

C-105 Attachment

13-3/8" cemented with 400 sacks class "C" cement, 2% CaCl₂ with 1/4# Flo-Cele per sack, cement circulated.

8-5/8" cemented with 350 sacks class "C" cement, 2% Calcium chloride, casing parted while cementing at 883 feet, tied casing together with slip over shoe, cemented with 125 sacks class "C" cement, 2% Calcium Chloride. WOC 12 hours, pressure up with 500# for thirty minutes, held okay.

5-1/2" cemented with 800 sacks class "H" 50-50 Poz-Mix cement 2% CaCl.