

NO. OF COPIES RECEIVED	
DISTRIBUTION	
SANTA FE	
FILE	
U.S.G.S.	
LAND OFFICE	
OPERATOR	

NEW MEXICO OIL CONSERVATION COMMISSION

JAN 31 11 43 AM '67

Form C-103  
Supersedes Old  
C-102 and C-103  
Effective 1-1-65

5a. Indicate Type of Lease
State <input checked="" type="checkbox"/> Fee <input type="checkbox"/>
5. State Oil & Gas Lease No.
K 3933

### SUNDRY NOTICES AND REPORTS ON WELLS

(DO NOT USE THIS FORM FOR PROPOSALS TO DRILL OR TO DEEPEN OR PLUG BACK TO A DIFFERENT RESERVOIR. USE "APPLICATION FOR PERMIT -" (FORM C-101) FOR SUCH PROPOSALS.)

1. OIL WELL <input checked="" type="checkbox"/> GAS WELL <input type="checkbox"/> OTHER <input type="checkbox"/>	7. Unit Agreement Name
2. Name of Operator McGrath & Smith, Inc.	8. Farm or Lease Name Chaveroo B State
3. Address of Operator 726 Vaughn Bldg., Midland, Texas	9. Well No. 1
4. Location of Well UNIT LETTER K 1980 FEET FROM THE S LINE AND 1980 FEET FROM THE W LINE, SECTION 32 TOWNSHIP 7S RANGE 33E NMPM.	10. Field and Pool, or Wildcat UNDESIGNATED Andres
15. Elevation (Show whether DF, RT, GR, etc.) 33 4467 OL 4457	12. County Roosevelt

16. Check Appropriate Box To Indicate Nature of Notice, Report or Other Data

NOTICE OF INTENTION TO:

SUBSEQUENT REPORT OF:

PERFORM REMEDIAL WORK <input type="checkbox"/>	PLUG AND ABANDON <input type="checkbox"/>	REMEDIAL WORK <input type="checkbox"/>	ALTERING CASING <input type="checkbox"/>
TEMPORARILY ABANDON <input type="checkbox"/>	CHANGE PLANS <input type="checkbox"/>	COMMENCE DRILLING OPERATIONS <input type="checkbox"/>	PLUG AND ABANDONMENT <input type="checkbox"/>
PULL OR ALTER CASING <input type="checkbox"/>	OTHER <input type="checkbox"/>	CASING TEST AND CEMENT JOBS <input checked="" type="checkbox"/>	OTHER <input type="checkbox"/>

17. Describe Proposed or Completed Operations (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work) SEE RULE 1103.

Spudded 12-5-66

CMTD 8 5/8 - 20# Csg at 373' with 140 sx Incor 8% followed by 50 sx Incor neat- all with 2% CaCl<sub>2</sub>. Cement Circulated.

Slurry vol. 358 Ft<sup>3</sup> at 50 degrees F (mixing temp.)  
Min Res Temp 99 degrees F

Cement in place 12 hrs. before testing with 1000 psi - held OK.

Compressive Strength of Incor 8% (Class C) 8% with 2% CaCl<sub>2</sub> after 12 hrs. is 500 psi at 100 degrees. Compressive Strength of Incor Neat (Class C) 8% with 2% CaCl<sub>2</sub> after 12 hrs. is 1200 psi 100 degrees F.

18. I hereby certify that the information above is true and complete to the best of my knowledge and belief.

SIGNED J.B. Taylor TITLE Engineer DATE Jan. 30, 1967

APPROVED BY [Signature] TITLE [Signature] DATE [Signature]

CONDITIONS OF APPROVAL, IF ANY: