

NO. OF COPIES RECEIVED	
DISTRIBUTION	
SANTA FE	
FILE	
U.S.G.S.	
LAND OFFICE	
OPERATOR	

NEW MEXICO OIL CONSERVATION COMMISSION

JAN 25 11 52 AM '67

Form C-103
Supersedes Old
C-102 and C-103
Effective 1-1-65

5a. Indicate Type of Lease State <input checked="" type="checkbox"/> Fee <input type="checkbox"/>
5. State Oil & Gas Lease No. K 3933

SUNDRY NOTICES AND REPORTS ON WELLS

(DO NOT USE THIS FORM FOR PROPOSALS TO DRILL OR TO DEEPEN OR PLUG BACK TO A DIFFERENT RESERVOIR.
USE "APPLICATION FOR PERMIT -" (FORM C-101) FOR SUCH PROPOSALS.)

1. OIL WELL <input checked="" type="checkbox"/> GAS WELL <input type="checkbox"/> OTHER <input type="checkbox"/>	7. Unit Agreement Name -
2. Name of Operator McGrath & Smith, Inc.	8. Farm or Lease Name Chaveroo B State
3. Address of Operator 726 Vaughn Building, Midland, Texas 79701	9. Well No. 2
4. Location of Well UNIT LETTER I, 1980 FEET FROM THE south LINE AND 660 FEET FROM THE east LINE, SECTION 31 TOWNSHIP 7-S RANGE 33-E NMPM.	10. Field and Pool, or Wildcat Chaveroo San Andres
15. Elevation (Show whether DF, RT, GR etc.) KB 4456, GL 4446	12. County Roosevelt

Check Appropriate Box To Indicate Nature of Notice or Report or Other Data
NOTICE OF INTENTION TO: SUBSEQUENT REPORT OF:

PERFORM REMEDIAL WORK <input type="checkbox"/>	PLUG AND ABANDON <input type="checkbox"/>	REMEDIAL WORK <input type="checkbox"/>	ALTERING CASING <input type="checkbox"/>
TEMPORARILY ABANDON <input type="checkbox"/>	CHANGE PLANS <input type="checkbox"/>	COMMENCE DRILLING OPNS. <input type="checkbox"/>	PLUG AND ABANDONMENT <input type="checkbox"/>
PULL OR ALTER CASING <input type="checkbox"/>	OTHER <input type="checkbox"/>	CASING TEST AND CEMENT JOBS <input checked="" type="checkbox"/>	

17. Describe Proposed or Completed Operations (Clearly state all pertinent details, and give pertinent dates including estimated date of starting any proposed work) SEE RULE 1108.

Spudded Dec. 15, 1966
Set 8-5/8 - 20# csg. at 574' - cemented w/190 sx - rounded
WOC 12 hrs. Tested with 1000 psi - held ok.
Cemented w/140 sx Incor. 8% gel followed by 50 sx Incor. w/2% calcium chloride.
Slurry Volume: 358 cu. ft at 40 deg. F. mixing temperature.
Cement circulated
Min. formation Temp. 99 deg. F.
Cement in place 12 hrs. before testing. Tested with 1000 psi - held ok.
Compressive strength of Incor. (Class C) 8% with 2% calcium chloride after 12 hrs. is 500 psi.
" " " " " neat " " " " " " 12 hrs. is 1200 psi.

18. I hereby certify that the information above is true and complete to the best of my knowledge and belief.

SIGNED <u>JB Taylor</u>	TITLE <u>Engineer</u>	DATE <u>1-24-67</u>
APPROVED BY <u></u>	TITLE <u></u>	DATE <u></u>
CONDITIONS OF APPROVAL, IF ANY:		