

PROPOSED MUD PROGRAM

South Four Lakes Well No. 10

DEPTH	MUD WEIGHT	VISCOSITY	FLUID LOSS	CL PPM	%SOLIDS	ADDITIVES
Surf - 400'	8.6-9.0 ppg	32-34 sec/1000 cc	-	-	-	Native Solids
400' - 4200'	10.0-10.2 ppg	30-32 sec/1000 cc	-	Saturated	-	Native Solids
4200' - 7000'	8.8-9.0 ppg	28-30 sec/1000 cc	-	-	-	
7000' - 9850'	9.0-9.4 ppg	34-38 sec/1000 cc	-	-	-	Salt Gel/Oil/Soltex 2% Oil
9850' - 10600'	9.2-9.5 ppg	34-40 sec/1000 cc	12 - 15 cc	-	-	Starch

The Mud Engineer shall include on each test report the materials used for the previous 24 hr. period. Twice weekly mail copies of the test reports to:

A. C. Sewell
4001 Penbrook
Odessa, Texas 79762

Send two copies of the Well Recap (Final Cost & Engineering Summaries) to A. C. Sewell at the above address.

RECEIVED

MAY 12 1992

CON HOBBY CENTER