

CEMENT PROGRAM (Also, See Exhibit F-1)

13 3/8" Casing: 440 sx Class "C" containing 2%  $\text{CaCl}_2$ . Cement circulated to surface.

8 5/8" Casing: 1200 sx Class "C" 35/65 Poz containing 3#/sx salt and 1#/sx Gilsonite. Tail in with 200 sx Class "C" containing 1%  $\text{CaCl}_2$ . Cement brought back to surface.

5 1/2" Casing: 800 sx Class "H" containing 3% KCl and .7% FL-20.

EXHIBIT F

Charles B. Gillespie, Jr.  
Hamilton Federal No. 3  
1880' FSL and 2080' FWL  
Section 33, T-15-S, R-35-E  
Lea County, New Mexico