

DISTRICT I

P.O. Box 1980, Hobbs, NM 88240

DISTRICT II

P.O. Box Drawer DD, Artesia, NM 88210

DISTRICT III

1000 Rio Brazos Rd., Aztec, NM 87410

OIL CONSERVATION DIVISION

P.O. Box 2088

Santa Fe, New Mexico 87504-2088

WELL API NO.	30-025-32800
5. Indicate Type of Lease	STATE <input checked="" type="checkbox"/> FEE <input type="checkbox"/>
6. State Oil / Gas Lease No.	
7. Lease Name or Unit Agreement Name	CENTRAL VACUUM UNIT
8. Well No.	193
9. Pool Name or Wildcat	
10. Elevation (Show whether DF, RKB, RT, GR, etc.) 3985'	

SUNDRY NOTICES AND REPORTS ON WELL
(DO NOT USE THIS FORM FOR PROPOSALS TO DRILL OR TO DEEPEN OR PLUG BACK TO A DIFFERENT RESERVOIR. USE "APPLICATION FOR PERMIT (FORM C-101) FOR SUCH PROPOSALS.)

1. Type of Well:	OIL WELL <input checked="" type="checkbox"/> GAS WELL <input type="checkbox"/> OTHER <input type="checkbox"/>
2. Name of Operator	TEXACO EXPLORATION & PRODUCTION INC.
3. Address of Operator	P.O. Box 46510, Denver Colorado 80201-6510
4. Well Location	Unit Letter <u>D</u> : <u>101</u> Feet From The <u>NORTH</u> Line and <u>534</u> Feet From The <u>WEST</u> Line Section <u>6</u> Township <u>18-S</u> Range <u>35-E</u> NMPM <u>LEA</u> COUNTY
10. Elevation (Show whether DF, RKB, RT, GR, etc.)	3985'

11. Check Appropriate Box to Indicate Nature of Notice, Report, or Other Data

NOTICE OF INTENTION TO:

PERFORM REMEDIAL WORK ☐ PLUG AND ABANDON ☐
TEMPORARILY ABANDON ☐ CHANGE PLANS ☐
PULL OR ALTER CASING ☐
OTHER: ☐

SUBSEQUENT REPORT OF:

REMEDIAL WORK ☐ ALTERING CASING ☐
COMMENCE DRILLING OPERATION ☐ PLUG AND ABANDONMENT ☐
CASING TEST AND CEMENT JOB ☐
OTHER: ☒ SPUD, SURF CSG, PROD CSG

12. Describe Proposed or Completed Operations (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work) SEE RULE 1103.

- NABORS RIG SPUD 11 INCH HOLE @ 3:00 PM 03-04-95. DRILLED TO 1460'. TD @ 1:00 AM 03-06-95.
- RAN 38 JOINTS OF 8-5/8" 24#, WC-50, STC CASING SET @ 1527'. RAN 10 CENTRALIZERS.
- DOWELL CEMENTED WITH 375 SACKS CLASS C W/ 4% GEL, 2% CACL2 (13.5 PPG, 1.74 CF/S). F/B 150 SACKS CLASS C W/ 2% CACL2 (14.8 PPG, 1.34 CF/S). PLUG DOWN @ 7:00 AM 03-06-95. CIRCULATED 77 SACKS.
- NU BOP & TESTED TO 1000#. TESTED CASING TO 1000# FOR 30 MINUTES FROM 8:45 PM TO 9:15 PM 03-06-95.
- WOC TIME 13-3/4 HOURS FROM 7:00 AM TO 8:45 PM 03-06-95. REQUIREMENTS OF RULE 107, OPTION 2:
1. VOLUME OF CEMENT SLURRY: LEAD 653 (CU. FT.), TAIL 201 (CU. FT.).
2. APPROX. TEMPERATURE OF SLURRY WHEN MIXED: 50 F.
3. EST. FORMATION TEMPERATURE IN ZONE OF INTEREST: 90 F.
4. EST. CEMENT STRENGTH AT TIME OF CASING TEST: 1633 PSI.
5. ACTUAL TIME CEMENT IN PLACE PRIOR TO TESTING: 13-3/4 HOURS.
- DRILLING 7 7/8 HOLE.
- DRILLED 7 7/8 HOLE TO 4800'. TD @ 9:30 PM 03-09-95.
- HLS RAN DLL-MSFL, LONG SPACED SONIC, SDL-DSN-GR FROM 3900' TO 4850'.
- RAN 118 JOINTS OF 15.5# WC-50, LTC CASING SET @ 4850'. 5 1/2"
- DOWELL CEMENTED WITH 700 SACKS 35/65 POZ CLASS H W/ 6% GEL, 5% SALT, 1/4# FLOCELE (12.8 PPG, 1.94 CF/S). F/B 200 SACKS 50/50 POZ CLASS H W/ 2% GEL, 5% SALT, 1/4# FLOCELE (14.2 PPG, 1.35 CF/S). PLUG DOWN @ 1:30 AM 03-11-95. CIRCULATED 25 SACKS.
- ND. RELEASE RIG @ 6:30 PM 03-11-95.
- PREP TO COMPLETE.

I hereby certify that the information above is true and complete to the best of my knowledge and belief.

SIGNATURE C.P. Basham / SRH TITLE Drilling Operations Mgr. DATE 3/27/95

TYPE OR PRINT NAME C. P. Basham Telephone No. (303)621-4851

(This space for State Use)

APPROVED BY GARY WINK TITLE FIELD REP. II DATE APR 03 1995

CONDITIONS OF APPROVAL, IF ANY:

Schlumberger

Dowell

CemDABE Cement Test Report

March 5, 1995

DATE OF TEST : 05-mar-1995

TEST NUMBER : NPD516800002

CUSTOMER : TEXACO
FIELD : LEA NM
WELL : C V U 193

CEMENT
Class : C
Blend :
Brand : LONESTAR
Plant : MARYNEAL

BASE FLUID

Density : 8.32 lb/gal
Volume : 6.32 gal/sk
Type : LO
Total liquid : 6.32 gal/sk

SLURRY

Density : 14.80 lb/gal
Yield : 1.32 ft³/sk

B.H.S.T. : 90.0 F

B.H.C.T. : 85.0 F

ADDITIVES		
Code	Concent.	Unit
S001	2.000	% BWOC

Rheometer type : Fann 35

Spring factor : 1.0

Bob No : 1

Rotor No : 1

Rheological model (Dial 1) : Bingham Plastic

T_y : 14.067 lbf/100ft²

P_o : 18.744 cP

Correlation coefficient : 0.999

Thickening Time : 2 hr 5 mn to 70 BC

API Schedule :

Set condition :

Consistometer serial number :

No Fluid Loss data available

No Free Water data available

Rheological data		
Temp. (F) :	75.0	0.0
R.P.M.	Dial 1	Dial 2
300.0	33.0	0.0
200.0	26.0	0.0
100.0	20.0	0.0
60.0	18.0	0.0
30.0	16.0	0.0
6.0	14.0	0.0
3.0	13.0	0.0
0.0	0.0	0.0
0.0	0.0	0.0
10 minutes Gel : 0.0		

Compressive strength		
PSI	Hours	Temp. (F)
600	6.0	90.0
1400	12.0	90.0
2000	24.0	90.0

Comment :

FIELD BLEND

CLASS C +2% S1

LOCATION WATER USED

SURFACE TAIL 1550' POD = 1:55