3 66.01

BJ SERVICES

CEMENT ANALYSIS

DATE: 5/25/95
COMPANY: HEYCO
WELL NAME: BUCKEYE
LEASE:
COUNTY: LEA
STATE: NEW MEXICO
STATION: HOBBS
REQUESTED BY:

2

REPORT NO.:
JOB TYPE: PRODUCTION
TEST TYPE: LAB
DEPTH (FT): 400
BHST(DEG. F.): 90
BHCT (DEG. F.): 80
WATER SOURCE: TAP
LAB

CEMENT ANALYSIS	LEAD
SLURRY TYPE:	CLASS C
ADDITIVES:	2% CACL .25PPS C.F.
DENISITY (PPG):	14.8
YIELD (CU.FT./SK):	1.33
WATER (GPS)	6.32
THICKENING TIME:	
FLUID LOSS (CC/30 MIN)	
FREE WATER :	
COMPRESSIVE STRENGTH:	
12 HOURS (PSI)	1650
24 HOURS (PSI)	
48 HOURS (PSI)	
72 HOURS (PSI)	
RHEOLOGY (CP)	
600 RPM	
300 RPM	
200 RPM	
100 RPM	
6 RPM	
3 RPM	
ANALYZED BY:	MIKE LEE

BJ SERVICES

RECEIVED

JUN 0 7 1990

OCD HOBBS
OFFICE