

CASING PROGRAM

We propose to use the following strings of Casing and to cement them as indicated:

Size of Hole	Size of Casing	Weight per foot	New or Second Hand	Depth	Sacks Cement
11"	8-5/8"	24	New	1-80'	600*
7-7/8"	2-7/8"	6.5	New	6850'	900**
	2-7/8"	6.5	New	6850'	

* 400 Sacks Class "C" 45 gel, followed by 200 Sacks Class "C" Neat. Use accelerator in neat.

** Externally clean casing & install centralizers over prospective pays. Cement with 300 Sacks Class "C" 45 gel, 45 salt and friction reducing agent, followed by 300 Sacks Class "C" 45 gel, followed by 300 Sacks Class "C" 45 gel.

FORMATION TOPS REFERRED

Anhydrite	1250'
Top of Salt	4500'
Base of salt	5500'
Water	6500'
San Andres	7500'
Glorieta	8500'
Blinberry	9500'
Total Depth	10600'