

PROPOSED CASING & CEMENTING PROGRAM

EVGSAU 3229-013

8 5/8" 24 lb/ft J-55 Surface Casing Set at 1560' - 12 1/4" Hole:

Circulate to surface with 1000 sx of Class "C" + 2% CaCl_2 .

Slurry Weight:	14.8 ppg
Slurry Yield:	1.32 ft ³ /sx
Water Requirement:	6.3 gals/sx

5 1/2" 15.5 lb/ft J-55 Production Casing Set at 4900' - 7 7/8" Hole:

Lead: 400 sx Class "C" + 20% Diacel D + 3% Salt. Desired TOC = Surface.

Slurry Weight:	12.0 ppg
Slurry Yield:	2.79 ft ³ /sx
Water Requirement:	16.1 gals/sx

Tail: 300 sx Class "C" Neat. Desired TOC = 4000'.

Slurry Weight:	14.8 ppg
Slurry Yield:	1.32 ft ³ /sx
Water Requirement:	6.3 gals/sx

RESERVE

1993

JOBS
OFFICE