

PROPOSED CASING & CEMENTING PROGRAM

EVGSAU 3202-021

8 5/8" 24 lb/ft J-55 Surface Casing Set at 1575' - 12 1/4" Hole:

Circulate to surface with 800 sx of Class "C" + 2%  $\text{CaCl}_2$ .

Slurry Weight:	14.8 ppg
Slurry Yield:	1.32 ft <sup>3</sup> /sx
Water Requirement:	6.3 gals/sx

5 1/2" 15.5 lb/ft J-55 Production Casing Set at 4900' - 7 7/8" Hole:

Lead: 500 sx Class "C" 65/35 Poz + 6% Gel + 3% Salt. Desired TOC = Surface.

Slurry Weight:	12.8 ppg
Slurry Yield:	1.85 ft <sup>3</sup> /sx
Water Requirement:	9.9 gals/sx

Tail: 350 sx Class "C" 50/50 Poz + 0.5% Halad-9 + 1.5%  $\text{CaCl}_2$ . Desired TOC = 4000'.

Slurry Weight:	14.6 ppg
Slurry Yield:	1.15 ft <sup>3</sup> /sx
Water Requirement:	5.0 gals/sx