

2-11-95

RU and run 11 jts 13-3/8" H-40 48# ST&C casing to 465'. Cement casing using 425 sx cement (225 sx "C" Lite plus additives, WT 13.5#, Y 1.74 and 200 sx "C" plus 2% CACL, Wt 14.8, Y 1.32). Plug did not pump and float did not hold. Circulated 200 sx cement to pit. WOC 4-3/4 hrs. Cut off casing, well on head, NU BOPE and test casing to 1,500 psi. Reduced hole size.

2-18-95

LD 8" DC's. Run 104 jts 8-5/8" J-55 ST&C (2 jts 32#, 56 jts 32# and 46 jts 24#) csg and set at 4,630'. Cement casing using 1,600 sx cement (1,400 sx 35/65 Poz C plus 6% gel plus 10% salt plus .25 pps Cello plus .2% Antifoam mixed at 12.4 ppg, Y 2.3 and 200 sc C, WT 14.8, Y 1.32). Bumped plug with 2,000 psi. Float held. Circ 270 sx cement to pit. WOC. Cut off 13-3/8" head and weld on 8-5/8" head. Reduce hole size.